



Synthesis and Characterization of ZnO Nanoparticles for Optoelectronic Applications

¹Vasudha Heshmati

¹Department of Electrical and Computer Engineering, Sundarban College of Technology Studies, Bangladesh

¹vasudha.heshmati@scts-bd.net

Peer Review Information

Submission: 05 Oct 2015

Revision: 15 Nov 2015

Acceptance: 30 Nov 2015

Keywords

ZnO nanoparticles, Sol-gel synthesis, Optoelectronics, Photoluminescence, UV-Visible spectroscopy

Abstract

Zinc oxide (ZnO) is a wide-band-gap semiconductor whose high exciton binding energy, optical transparency, defect-sensitive luminescence and compatibility with low-cost wet-chemical processing make it attractive for ultraviolet photodetectors, light-emitting structures, transparent electronics and photovoltaic interfaces. This methodology paper proposes a reproducible sol-gel/precipitation route for synthesizing ZnO nanoparticles from zinc acetate, followed by structural, morphological, optical, luminescence and electrical characterization. The procedure emphasizes controlled precursor concentration, alkaline hydrolysis, ageing, washing and calcination because these parameters strongly influence crystallite size, defect chemistry and optical band gap. X-ray diffraction (XRD) is used to verify the hexagonal wurtzite phase and estimate crystallite size; scanning/transmission electron microscopy (SEM/TEM) is used for morphology and particle-size assessment; UV-Visible spectroscopy is used to determine the absorption edge and optical band gap; photoluminescence (PL) is used to distinguish near-band-edge emission from defect-related visible emission; and impedance/current-voltage measurements are proposed for electronic response. Literature published no later than 2015 indicates that chemically synthesized ZnO commonly exhibits nanoscale wurtzite crystallites, a near-UV absorption edge, room-temperature excitonic emission and processing-dependent defect luminescence. The methodology therefore provides a compact framework for linking synthesis conditions to optoelectronic quality while avoiding unsupported claims of device performance.

Introduction

Zinc oxide is an II-VI compound semiconductor with a direct band gap near 3.3-3.4 eV and an exciton binding energy of about 60 meV at room temperature. These characteristics support strong near-band-edge optical transitions and have made ZnO a major candidate for blue/ultraviolet optoelectronics, transparent conductors, sensors and nanostructured electronic devices (Özgür et al., 2005; Klingshirn, 2007). ZnO also possesses a non-centrosymmetric wurtzite lattice, giving useful

piezoelectric behavior alongside its semiconductor properties (Wang, 2004). From a device-processing perspective, a major advantage is that ZnO can be produced in many nanoscale morphologies using comparatively inexpensive wet-chemical routes rather than exclusively high-vacuum growth (Baruah & Dutta, 2009; Djurišić et al., 2010).

At the nanoscale, particle size, surface chemistry, native defects and thermal treatment can substantially alter absorption,

photoluminescence and charge transport. Early colloidal work demonstrated controlled growth of ZnO particles only a few nanometres in size from zinc acetate-based chemistry (Meulenkamp, 1998). Later studies established that the optical and electrical response of ZnO depends not only on crystallite size but also on vacancies, impurities, surfaces and interfaces; consequently, careful characterization is essential before assigning a nanomaterial to an optoelectronic function (Janotti & Van de Walle, 2009). Sol-gel and related precipitation routes are especially useful in methodology studies because precursor concentration, base-to-zinc ratio, ageing and calcination temperature can be systematically varied (Dejene et al., 2011; Omri et al., 2014).

The objective of this paper is to define a practical synthesis and characterization protocol for ZnO nanoparticles intended for advanced optoelectronic investigation. Rather than presenting fabricated experimental data, the study specifies measurable acceptance criteria and literature-supported response ranges. This makes the protocol suitable as a methodology paper and as a foundation for subsequent laboratory validation, optimization and device integration.

Literature Review

The literature up to 2015 shows a clear progression from basic colloidal synthesis to structure-property engineering and optoelectronic device relevance. Meulenkamp (1998) reported zinc acetate-derived nanoparticles and demonstrated that wet chemistry can control nanocrystal growth. Wang (2004) summarized the unusually rich family of

ZnO nanostructures and connected their semiconducting and piezoelectric properties with nanoscale device opportunities. Özgür et al. (2005) and Klingshirm (2007) consolidated the electronic and optical basis for ZnO, particularly the wide band gap, high exciton binding energy and challenges associated with stable conductivity control. Baruah and Dutta (2009) highlighted hydrothermal chemistry as a low-temperature and comparatively simple route to controlled nanostructures, while Janotti and Van de Walle (2009) emphasized that native-defect interpretations must be treated carefully when explaining electrical behavior.

Application-focused reviews subsequently linked material synthesis with photodetectors, LEDs and solar-cell structures (Djurišić et al., 2010). Experimental studies are equally important for defining a methodology. Dejene et al. (2011) showed that alkali-to-zinc ratio in sol-gel processing changes the optical properties of ZnO nanoparticles. Talam et al. (2012) used precipitation synthesis and combined XRD, electron microscopy, UV-Visible absorption and PL to establish a complete characterization sequence. Foo et al. (2014) demonstrated that sol-gel-derived seed layers and hydrothermal growth can produce wurtzite ZnO with measurable changes in band gap and crystallinity, whereas Omri et al. (2014) showed that thermal treatment changes crystallite/particle size, luminescence and optical band gap. These studies collectively justify a methodology in which synthesis variables and post-annealing are controlled together and the structural, optical and electrical results are interpreted as a linked dataset rather than in isolation.

Table 1. Selected literature supporting the proposed methodology (all publications ≤ 2015)

Study	Focus	Methodological contribution
Meulenkamp (1998)	Wet-chemical growth of ZnO nanoparticles	Established zinc acetate-based nanoscale synthesis and growth control.
Wang (2004)	ZnO nanostructures and applications	Linked nanoscale morphology with electronic, optical and piezoelectric functions.
Özgür et al. (2005)	ZnO materials and devices review	Summarized wide-band-gap and excitonic advantages for optoelectronics.
Baruah & Dutta (2009)	Hydrothermal ZnO growth	Supported low-temperature solution processing and morphology control.
Dejene et al. (2011)	Sol-gel ZnO nanoparticles	Showed that base/precursor ratio affects optical response.
Talam et al. (2012)	Precipitated ZnO nanoparticles	Demonstrated combined XRD, microscopy, UV-Vis and PL characterization.
Foo et al. (2014)	Sol-gel/hydrothermal ZnO	Connected solvent/seed conditions with

	nanorods	crystallinity and optical band gap.
Omri et al. (2014)	Thermal treatment of sol-gel ZnO	Demonstrated annealing-dependent size, band gap, PL and electrical response.

Methodology

The proposed workflow is designed for repeatability and can be executed using standard nanomaterials laboratory facilities. Zinc acetate dihydrate is selected as the zinc precursor because acetate-based chemistry has been widely used for ZnO nanoparticle synthesis (Meulenkamp, 1998; Dejene et al., 2011). The base-mediated hydrolysis route is combined with controlled drying and calcination to obtain phase-pure ZnO suitable for optical and electronic testing.

Step 1 - Reagent preparation. Prepare a 0.1 M solution of zinc acetate dihydrate in absolute ethanol (or 2-methoxyethanol when higher solubility is required). Separately prepare 0.2 M NaOH in ethanol. Use analytical-grade reagents and deionized water only for washing.

Step 2 - Sol formation and hydrolysis. Heat the zinc precursor to approximately 60 °C under magnetic stirring. Add the NaOH solution dropwise until a transparent-to-milky sol forms. Maintain a NaOH:Zn molar ratio near 2:1 as the baseline condition; ratio variation can be included as an optimization factor because optical properties are sensitive to alkaline conditions (Dejene et al., 2011).

Step 3 - Ageing. Continue stirring for 60 min and age the sol for 12-24 h at room temperature. Ageing allows hydrolysis/condensation to proceed and improves reproducibility of nucleation and particle growth.

Step 4 - Separation and washing. Centrifuge the precipitate, discard the supernatant and wash the solid three times with ethanol and then deionized water to reduce acetate and alkali residues. Dry the cleaned material at 80 °C for 8-12 h.

Step 5 - Calcination. Calcine the dried powder in air at 400, 450 and 500 °C for 2 h using a controlled heating rate (about 5 °C min⁻¹). Multiple temperatures are recommended because annealing can increase crystallinity while modifying particle size, band gap and defect-related PL (Omri et al., 2014).

Step 6 - Structural and morphological characterization. Record XRD over $2\theta = 20-80^\circ$ using Cu K α radiation. Confirm the wurtzite reflections and estimate crystallite size with the Scherrer relation $D = K\lambda/(\beta \cos\theta)$. Examine morphology using SEM; use TEM/HRTEM where available to determine individual particle size, agglomeration and lattice fringes. Talam et al. (2012) demonstrated the value of combining diffraction and electron microscopy rather than using XRD size alone.

Step 7 - Optical and luminescence characterization. Measure UV-Visible absorbance from 300-800 nm and obtain the direct optical band gap from a Tauc plot of $(\alpha h\nu)^2$ versus $h\nu$. Record room-temperature PL using near-UV excitation. Distinguish the near-band-edge UV emission from broad visible defect-related emission; the latter should be interpreted cautiously because multiple intrinsic and extrinsic defects can contribute (Janotti & Van de Walle, 2009).

Step 8 - Electrical/optoelectronic evaluation. Press the nanopowder into pellets or deposit a nanoparticle film on glass/ITO. Measure current-voltage behavior in dark and under UV illumination and, where equipment permits, impedance from approximately 40 Hz to 1-2 MHz. Photocurrent enhancement, stable repeatability and low visible absorption are useful screening criteria for UV photodetector or transparent-electronics studies (Djurišić et al., 2010; Omri et al., 2014).




Figure 1. Proposed synthesis and characterization workflow for ZnO nanoparticles intended for optoelectronic evaluation.

Table 2. Characterization plan and acceptance indicators

Technique	Primary measurement	Acceptance / interpretation
XRD	Phase, crystallinity, crystallite size	Wurtzite ZnO; no strong impurity peaks; nanoscale crystallite size.
SEM/TEM	Morphology and particle size	Nanoparticles/nanograins with quantified mean size and agglomeration.
UV-Vis	Absorption edge and E_g	Strong near-UV absorption; direct E_g typically near bulk/nanoscale ZnO range.
PL	Recombination and defects	Near-band-edge UV emission plus processing-dependent visible defect band.
I-V / impedance	Charge transport and UV response	Reproducible conductivity; measurable light-dependent response where films/pellets are suitable.

Results

Methodological status of the results. No original laboratory dataset was supplied for this paper. Accordingly, the values below are literature-supported targets and expected trends that should be replaced by measured values after the proposed experiment is performed. This distinction prevents literature values from being presented as newly obtained experimental data.

Structurally, successful synthesis should yield the hexagonal wurtzite ZnO phase, consistent with the broad ZnO literature and with chemically prepared nanoparticle studies (Talam et al., 2012; Omri et al., 2014). The strongest XRD reflections are expected in the region associated with the (100), (002) and (101) planes. Increasing calcination temperature should generally sharpen diffraction peaks, indicating improved crystallinity, but may also increase crystallite size through grain growth. Electron microscopy is expected to show nanoscale primary particles with some agglomeration because high-surface-energy oxide nanoparticles readily cluster during drying.

Optically, ZnO should exhibit a strong absorption edge in the near-UV. Talam et al. (2012) reported an absorption feature near 355 nm for precipitated ZnO, while Omri et al.

(2014) observed an annealing-dependent optical band gap of approximately 3.34 to 3.21 eV and a strong UV luminescence band around 384 nm for material treated at 500 °C. Foo et al. (2014) likewise reported band-gap values around the low-3-eV range for sol-gel/hydrothermally prepared ZnO nanostructures. Therefore, a direct band gap roughly around 3.2-3.4 eV is a reasonable quality-control window for undoped ZnO prepared by the proposed route, with exact values determined by particle size, strain, defects and thermal history.

Photoluminescence should contain a near-band-edge ultraviolet component and may contain broad visible emission. Visible green/yellow bands are often used as qualitative indicators of defect-related recombination, but they should not be assigned to one defect solely from PL peak position because defect energetics in ZnO are complex (Janotti & Van de Walle, 2009; Djurišić et al., 2010). For optoelectronic screening, a relatively strong near-band-edge signal, low uncontrolled visible absorption and reproducible photoresponse are preferable. The most useful optimization outcome is therefore not a single maximum intensity; it is a balanced condition that yields phase-pure ZnO, controlled particle size, stable band gap and repeatable light-dependent electrical behavior.

Table 3. Literature-supported result ranges/trends for validating the proposed experiment

Parameter	Expected result / trend	Literature basis
Crystal structure	Hexagonal wurtzite	Wang, 2004; Talam et al., 2012
Crystallite / particle scale	Nanoscale; often tens of nm after calcination	Meulenkamp, 1998; Omri et al., 2014
Optical band gap	Approximately 3.2-3.4 eV for typical undoped nanostructured ZnO	Foo et al., 2014; Omri et al., 2014
PL response	Near-UV band-edge emission + possible visible defect band	Klingshirn, 2007; Talam et al., 2012
Optoelectronic relevance	UV detection, LEDs, transparent electronics, photovoltaic interfaces	Özgür et al., 2005; Djurišić et al., 2010

Conclusion and Discussion

A controlled sol-gel/precipitation methodology provides a practical route for synthesizing ZnO nanoparticles for optoelectronic research. The critical experimental variables are precursor/base ratio, reaction temperature, ageing, washing and calcination temperature. These parameters should be optimized together because they determine phase purity, grain growth, surface defects and ultimately optical/electrical response. The proposed characterization sequence - XRD, SEM/TEM, UV-Visible spectroscopy, PL and electrical/photoresponse measurements - is sufficient to establish whether the material has the structural and optoelectronic characteristics expected of ZnO. Literature through 2015 consistently supports wurtzite phase formation by solution processing, near-UV absorption and emission, and strong sensitivity of band gap and luminescence to synthesis and annealing conditions (Dejene et al., 2011; Talam et al., 2012; Omri et al., 2014). For advanced applications, the methodology should next be extended to thin-film deposition, controlled doping and device-level contact engineering. Stable p-type doping and the interpretation of defects remain major scientific challenges, so device conclusions should be based on direct electrical and spectroscopic measurements rather than inferred from synthesis alone (Özgür et al., 2005; Janotti & Van de Walle, 2009). In this sense, the proposed protocol is best viewed as a reproducible materials-screening platform: it identifies synthesis conditions that produce optically active, phase-pure ZnO and generates the evidence required before the nanoparticles are integrated into UV photodetectors, light-emitting structures, transparent electronics or photovoltaic systems. Reproducibility depends on controlling variables that are sometimes treated as minor details in wet-chemical synthesis. The zinc precursor concentration, actual NaOH concentration, addition rate, solution temperature, stirring history, ageing time and washing sequence should therefore be recorded for every batch. At least three independent synthesis batches should be prepared at the selected optimum condition. XRD-derived crystallite size should be reported together with instrumental broadening information where possible, while microscopy-based particle size should be obtained from a statistically meaningful number of particles rather than a single field of view. Agreement between XRD, TEM/SEM and optical trends is more important than exact equality because each technique

measures a different physical quantity. Optical measurements require similar care. UV-Visible spectra should be baseline-corrected against the same solvent or substrate used for the sample, and the Tauc-fit region should be chosen consistently across samples. Photoluminescence intensity is strongly affected by excitation power, slit width, sample mass and optical geometry; consequently, spectra should be collected under identical instrumental settings before relative intensity is compared. Visible PL should be described as defect-related emission unless a specific defect assignment is independently supported. This caution is consistent with the defect-physics discussion of Janotti and Van de Walle (2009) and the device-focused review by Djurišić et al. (2010). For the electrical stage, powder conductivity alone does not establish device suitability. Film thickness, porosity, electrode spacing, contact metal and illumination power can dominate the measured current. A simple UV-response test should therefore include dark current, illuminated current, repeated on/off cycles and a fixed measurement geometry. If the photocurrent is unstable, the material should be re-evaluated for surface adsorption, defect density and contact effects before a photodetector claim is made. When impedance is used, fitting should be accompanied by a stated equivalent circuit and residual/error assessment rather than reporting only a semicircular Nyquist plot. The principal limitation of the proposed study is that it is a materials-screening methodology and not a completed device demonstration. The optimum nanoparticle condition identified by XRD, UV-Visible and PL may change after film deposition because drying, substrate interaction and post-deposition annealing alter microstructure. Likewise, the sol-gel route is attractive for cost and simplicity but can produce agglomeration and batch-to-batch variation if moisture and base addition are poorly controlled. These limitations do not reduce the value of the method; rather, they define the next validation stage: optimize nanoparticle synthesis first, then transfer the best condition to a controlled thin-film process and finally measure device-specific figures of merit such as responsivity, response time, external quantum efficiency or transparency/conductivity trade-off.

References

- Baruah, S., & Dutta, J. (2009). Hydrothermal growth of ZnO nanostructures. *Science and Technology of Advanced Materials*, 10(1), 013001. DOI: 10.1088/1468-

6996/10/1/013001

[https://doi.org/10.1088/1468-](https://doi.org/10.1088/1468-6996/10/1/013001)

6996/10/1/013001

Dejene, F. B., Ali, A. G., Swart, H. C., Botha, R. J., Roro, K., Coetsee, L., & Biggs, M. M. (2011). Optical properties of ZnO nanoparticles synthesized by varying the sodium hydroxide to zinc acetate molar ratios using a sol-gel process. *Open Physics*, 9(5), 1321-1326. DOI: 10.2478/s11534-011-0050-3
<https://doi.org/10.2478/s11534-011-0050-3>

Djurišić, A. B., Ng, A. M. C., & Chen, X. Y. (2010). ZnO nanostructures for optoelectronics: Material properties and device applications. *Progress in Quantum Electronics*, 34(4), 191-259. DOI: 10.1016/j.pquantelec.2010.04.001
<https://doi.org/10.1016/j.pquantelec.2010.04.001>

Foo, K. L., Hashim, U., Muhammad, K., & Voon, C. H. (2014). Sol-gel synthesized zinc oxide nanorods and their structural and optical investigation for optoelectronic application. *Nanoscale Research Letters*, 9, 429. DOI: 10.1186/1556-276X-9-429
<https://doi.org/10.1186/1556-276X-9-429>
Janotti, A., & Van de Walle, C. G. (2009). Fundamentals of zinc oxide as a semiconductor. *Reports on Progress in Physics*, 72(12), 126501. DOI: 10.1088/0034-4885/72/12/126501
<https://doi.org/10.1088/0034-4885/72/12/126501>

Klingshirn, C. (2007). ZnO: Material, physics and applications. *ChemPhysChem*, 8(6), 782-803. DOI: 10.1002/cphc.200700002
<https://doi.org/10.1002/cphc.200700002>

Meulenkamp, E. A. (1998). Synthesis and growth of ZnO nanoparticles. *The Journal of Physical Chemistry B*, 102(29), 5566-5572. DOI: 10.1021/jp980730h
<https://doi.org/10.1021/jp980730h>

Omri, K., Najeh, I., Dhahri, R., El Ghoul, J., & El Mir, L. (2014). Effects of temperature on the optical and electrical properties of ZnO nanoparticles synthesized by sol-gel method. *Microelectronic Engineering*, 128, 53-58. DOI: 10.1016/j.mee.2014.05.029
<https://doi.org/10.1016/j.mee.2014.05.029>

Özgür, Ü., Alivov, Y. I., Liu, C., Teke, A., Reshchikov, M. A., Doğan, S., Avrutin, V., Cho, S.-J., & Morkoç, H. (2005). A comprehensive review of ZnO materials and devices. *Journal of Applied Physics*, 98(4), 041301. DOI: 10.1063/1.1992666
<https://doi.org/10.1063/1.1992666>

Talam, S., Karumuri, S. R., & Gunnam, N. (2012). Synthesis, characterization, and spectroscopic properties of ZnO nanoparticles. *ISRN Nanotechnology*, 2012, 372505. DOI: 10.5402/2012/372505
<https://doi.org/10.5402/2012/372505>