



Synthesis and Characterization of ZnO Nanostructures for Sensor Devices

¹Sudarshan Ekanayake

¹Department of Computer Science and Engineering, Tonle Sap Institute of Engineering and Commerce

¹sudarshan.ekanayake@tsiec-kh.org

Peer Review Information

Submission: 02 Jan 2016

Revision: 16 Feb 2016

Acceptance: 30 March 2016

Keywords

ZnO nanostructures,
hydrothermal synthesis,
nanorods, gas sensor,
material characterization

Abstract

Zinc oxide (ZnO) is a wide-band-gap n-type semiconductor whose high surface-to-volume ratio, chemical stability, defect-sensitive conductivity, optical response and compatibility with low-cost solution processing make it a strong platform for miniaturized sensors. This methodology paper proposes a reproducible route for synthesizing vertically oriented ZnO nanorods and evaluating their suitability as resistive sensor elements. A seeded hydrothermal method is selected because it enables growth below 100 °C, avoids vacuum equipment and permits direct deposition on insulating or electrode-patterned substrates. The experimental design uses zinc nitrate hexahydrate and hexamethylenetetramine (HMTA) as equimolar growth precursors, followed by washing, controlled annealing and multitechnique characterization using X-ray diffraction (XRD), scanning electron microscopy (SEM), energy-dispersive X-ray spectroscopy (EDS), UV-visible spectroscopy and photoluminescence (PL). For device evaluation, the nanorod layer is integrated with interdigitated electrodes and exposed to calibrated ethanol concentrations as a model reducing gas while resistance, response, recovery, selectivity and repeatability are measured as functions of concentration and operating temperature. The approach is grounded in literature available up to 2016 and is designed to separate structure–property relationships from fabrication variability. Expected outcomes include single-phase wurtzite ZnO, preferential c-axis growth, nanoscale rod diameters, a near-band-edge optical response, and a measurable resistance decrease in the presence of ethanol. The proposed protocol is adaptable to NO₂, H₂S, UV and biosensing formats and provides a practical framework for linking synthesis conditions, surface morphology and sensor performance without relying on expensive fabrication facilities.

Introduction

ZnO has attracted sustained attention in sensor research because it combines a direct band gap of approximately 3.37 eV, a large exciton binding energy, high electron mobility, piezoelectricity and a surface chemistry that is strongly influenced by adsorbed oxygen and target molecules. When ZnO dimensions are reduced to the nanoscale, a greater fraction of

atoms lies near the surface, so adsorption-induced charge transfer can modulate a comparatively large fraction of the conducting channel. This feature is particularly advantageous for resistive gas sensors, photodetectors and biosensor interfaces. Reviews of ZnO sensors have therefore emphasized one-dimensional forms such as

nanorods and nanowires, which offer high aspect ratio, direct electrical pathways and straightforward integration with planar electrodes (Wei, Pan, & Huang, 2011; Kumar et al., 2015).

The choice of synthesis route is critical because sensing behavior is not determined only by chemical composition. Crystallite size, exposed crystal facets, defect density, rod diameter, porosity, orientation, interparticle junctions and electrode geometry all affect resistance and adsorption kinetics. Vayssieres (2003) demonstrated that ordered ZnO nanorod and nanowire arrays could be grown from aqueous solutions at moderate temperature by controlling nucleation and interfacial processes. Greene et al. (2005) subsequently showed that textured ZnO seed layers provide a general route to vertical nanowire arrays. These solution-based approaches are especially useful for methodology-focused sensor studies because they lower equipment requirements while allowing independent control of seed density, precursor concentration, temperature and growth duration.

Sensor-device studies before 2016 established that ZnO nanostructures can detect diverse chemical and physical stimuli. Hydrothermally produced ZnO nanorods were reported for H₂S and ethanol detection (Wang, Chu, & Wu, 2006; Xu et al., 2006), while electrospun nanowires showed high ethanol sensitivity at elevated temperature (Wu, Ting, & Huang, 2009). Ahn et al. (2009) used on-chip nanowire bridges to improve NO₂ response, and Su et al. (2010) demonstrated strong ultraviolet photoresponse from hydrothermally grown ZnO nanorods. Such studies indicate that the same material platform can be adapted to multiple transduction mechanisms, but they also show that device performance depends strongly on morphology and processing.

The objective of this paper is to define a compact, step-by-step methodology for the synthesis, characterization and sensor integration of ZnO nanorods using laboratory-accessible methods. The specific experimental demonstration is a chemiresistive ethanol sensor, selected because it provides a convenient model for studying oxygen-mediated surface reactions in n-type ZnO. The protocol is nevertheless designed so that the sensing layer can later be tested against oxidizing gases, UV radiation or biomolecular interfaces. Since no original laboratory data are supplied with this methodology paper, the Results section reports expected structural signatures, benchmark

ranges and decision criteria derived from prior literature rather than presenting fabricated measurements.

Literature Review

Early work on aqueous ZnO growth established the foundation for low-temperature sensor fabrication. Vayssieres (2003) showed that arrays of ZnO rods and wires could be generated without templates or surfactants by controlling aqueous nucleation and growth. Greene et al. (2005) refined seeded solution growth, demonstrating that textured ZnO nanoparticles on a substrate guide vertically aligned nanowire. These studies are methodologically important because direct growth on a device substrate reduces the handling and random placement problems associated with transferring pre-synthesized nanostructures.

The relationship between ZnO morphology and gas response was demonstrated by several sensor studies. Wang, Chu, and Wu (2006) prepared hydrothermal ZnO nanorods and reported detection of H₂S at very low concentration, including room-temperature response under suitable preparation conditions. Xu et al. (2006) also used hydrothermal synthesis and found that nanorods showed improved sensitivity and stability compared with conventional ZnO, while catalytic modification could further tune selectivity. These results support the selection of hydrothermal growth when the experimental goal is to correlate rod morphology with gas-induced resistance changes.

Device architecture can magnify or suppress the intrinsic response of the sensing material. Wu, Ting, and Huang (2009) electrospun ZnO nanowires directly across interdigitated electrodes and observed strong ethanol response, illustrating the benefit of minimizing transfer steps and maximizing accessible surface. In the same year, Ahn et al. (2009) created ZnO nanowire air bridges between electrodes; the sensor showed high NO₂ response near 225 °C, attributed to modulation at both nanowire surfaces and nanowire junctions. These findings justify using interdigitated electrodes and emphasize the need to report electrode spacing and nanostructure connectivity as part of the methodology.

The versatility of ZnO extends beyond chemical gas sensing. Su et al. (2010) fabricated hydrothermal ZnO nanorod UV photosensors and attributed enhanced photoresponse to the high surface-to-volume ratio and surface

trapping processes. The broad review by Wei, Pan, and Huang (2011) summarized gas, chemical, biological, UV and pH sensor concepts and identified sensitivity-controlling factors such as dimensions, doping, functionalization and contact structure. This cross-application evidence strengthens the case for a common characterization package—XRD, electron microscopy, optical spectroscopy and electrical testing—before selecting a specific sensing mode.

By 2013–2015, literature increasingly focused on deliberate morphology control. Rai, Kwak, and Yu (2013) showed that solvothermal precursor chemistry could produce different ZnO morphologies and that gas-sensing behavior was morphology dependent. Lupan, Pauporte, and Chow (2014) reviewed low-temperature hydrothermal and electrochemical routes for ZnO sensor structures, emphasizing their low cost and device compatibility. Kumar et al. (2015) reviewed ZnO nanostructures for

NO₂ sensing and concluded that morphology, particle size, annealing conditions, humidity and operating temperature are central determinants of response, response time, recovery and selectivity. These conclusions motivate a factorial experimental design rather than evaluating a single synthesis condition.

Research available in 2016 further broadened the sensing context. Tereshchenko et al. (2016) reviewed optical biosensors based on ZnO nanostructures and highlighted the roles of surface properties, defects and biomolecule immobilization. Hahm (2016) discussed one-dimensional ZnO in electrical, electrochemical and fluorescence-based biosensing and emphasized the combination of reduced dimensions and intrinsic optical properties. Although the present methodology tests a gas-sensing format, these studies indicate that optimization of crystallinity, surface defect density and nanoscale geometry have value across sensor categories.

Table 1. Representative ZnO nanostructure sensor literature used to design the methodology

Reference	ZnO form / method	Sensor focus	Methodological implication
Vayssieres (2003)	Aqueous nanorod/nanowire arrays	General functional films	Low-temperature solution growth is scalable.
Wang et al. (2006)	Hydrothermal nanorods	H ₂ S / ethanol	Preparation conditions strongly affect selectivity.
Wu et al. (2009)	Electrospun nanowires	Ethanol	Direct bridging of electrodes can enhance response.
Ahn et al. (2009)	On-chip nanowire bridges	NO ₂	Junction and depletion effects influence sensitivity.
Su et al. (2010)	Hydrothermal nanorods	UV	High surface area improves photoresponse.
Rai et al. (2013)	Solvothermal nanostructures	Gas sensing	Morphology is a controlled performance variable.
Kumar et al. (2015)	Multiple ZnO morphologies	NO ₂ review	Annealing, size, humidity and temperature require control.

Methodology

1. Experimental design and materials

The study is designed as a controlled synthesis–structure–performance experiment. Three independent growth batches should be prepared under identical nominal conditions to assess reproducibility. A secondary annealing-temperature series (300, 400 and 500 °C for 1 h) is recommended to determine whether improved crystallinity compensates for loss of surface defects. Analytical-grade zinc nitrate hexahydrate [Zn(NO₃)₂·6H₂O], HMTA

(C₆H₁₂N₄), zinc acetate dihydrate, monoethanolamine, 2-propanol or ethanol, deionized water and laboratory-grade ethanol vapor are required. Alumina or glass substrates carrying Au/Pt interdigitated electrodes are preferred for gas testing; plain glass or silicon pieces may be processed in parallel for optical and SEM analysis.

Step-by-step synthesis of ZnO nanorods

Step 1 – Substrate cleaning. Cut substrates to approximately 10 × 10 mm. Ultrasonicate sequentially in detergent solution, deionized

water, acetone and 2-propanol for about 10 min each, then dry with clean air or nitrogen. The purpose is to remove organics that would create nonuniform nucleation or unstable electrode contacts.

Step 2 – ZnO seed-layer preparation. Prepare a 0.02–0.05 M zinc acetate solution in ethanol or 2-propanol with a small amount of monoethanolamine as stabilizer. Spin-coat at approximately 2500–3000 rpm for 30 s, dry at 100–150 °C for 10 min, and repeat for three cycles. Heat the seeded substrate at 300–350 °C for about 30 min to generate adherent ZnO nuclei. Seeded growth is selected because textured ZnO nuclei promote aligned solution growth (Greene et al., 2005).

Step 3 – Hydrothermal growth solution. Prepare separate aqueous solutions of zinc nitrate hexahydrate and HMTA and mix them to obtain equal final concentrations of 25 mM. A total volume of 100 mL is sufficient for several small substrates. HMTA slowly supplies hydroxide ions and buffers the solution, enabling controlled ZnO precipitation rather than rapid bulk formation.

Step 4 – Nanorod growth. Place the seeded substrates face-down or vertically in a covered

glass bottle or Teflon-lined vessel containing the precursor solution. Maintain at 90 °C for 4 h. Avoid placing substrates flat at the bottom where homogeneous precipitate can settle. A growth-temperature window of about 80–95 °C may be explored if rod length requires adjustment, consistent with the low-temperature solution-growth rationale established by Vayssieres (2003) and later sensor studies.

Step 5 – Washing and drying. Remove the substrates, rinse gently with deionized water to eliminate residual salts and loosely attached particles, and dry at 80–100 °C. Do not rub the active area because mechanical contact can remove nanorods.

Step 6 – Controlled annealing. Divide equivalent samples into 300, 400 and 500 °C annealing groups for 1 h in air with a moderate ramp rate (about 5 °C min⁻¹). The 400 °C condition is the primary candidate. Annealing should be reported explicitly because it can improve crystal order while also modifying oxygen vacancies and adsorption sites that contribute to sensing.




Figure 1. Proposed experimental workflow for ZnO nanorod synthesis, characterization and sensor evaluation (original schematic).

2. Structural, morphological and optical characterization

XRD should be recorded over $2\theta = 20\text{--}80^\circ$ using Cu K α radiation. Phase identification is performed against the hexagonal wurtzite ZnO pattern, with particular attention to the (100), (002) and (101) reflections. A strong (002) peak relative to other reflections is used as evidence of preferential c-axis orientation. Crystallite size may be estimated from the dominant peak using the Scherrer equation, while recognizing that the value represents coherent diffraction domain size rather than the physical rod diameter.

SEM is used to measure rod diameter, length, areal density, alignment and surface coverage. At least five fields from different substrate regions should be imaged, and a minimum of 50 rods should be measured for diameter statistics. EDS is used as a compositional check for Zn and O and to screen for unexpected contaminants.

UV-visible spectra are used to estimate the optical absorption edge and approximate band gap through a Tauc plot for a direct transition. PL at room temperature is recorded to compare near-band-edge UV emission with broad visible defect-related emission. The intention is not to minimize all defects: gas sensing may benefit from surface-related states, so PL is interpreted together with electrical response rather than as a stand-alone quality score.

Sensor-device fabrication and gas-testing protocol

Where ZnO is grown directly on interdigitated electrodes (IDEs), the active area is masked during seed coating so that bond pads remain clean. If growth is performed on a separate substrate, a controlled ZnO suspension may be drop-cast across IDEs, but direct growth is preferred because it reduces uncontrolled contact resistance. The device is mounted in a sealed test chamber with electrical

feedthroughs, gas inlet/outlet and a temperature-controlled stage. A constant bias of approximately 1–5 V is applied while resistance or current is recorded continuously. Before each run, the sensor is stabilized in dry air until the baseline drift is less than 2% over 10 min.

Ethanol is introduced at nominal concentrations of 10, 25, 50, 100, 250 and 500 ppm using certified gas mixtures or calibrated vapor dilution. Tests are repeated at 150, 200, 250, 300 and 350 °C to identify the operating

temperature that maximizes response while preserving acceptable recovery. For an n-type ZnO sensor exposed to a reducing gas, adsorbed oxygen species initially withdraw electrons from the surface, producing a depletion layer and relatively high resistance. Ethanol reacts with adsorbed oxygen and returns electrons to ZnO, decreasing resistance. This oxygen-mediated mechanism is consistent with the wider body of ZnO gas-sensor literature summarized by Kumar et al. (2015).

Table 2. Core experimental parameters for the proposed methodology

Stage	Parameter	Proposed setting	Control / rationale
Seed layer	Zinc acetate concentration	0.02–0.05 M	Uniform nucleation without thick film formation
Growth	Zn(NO ₃) ₂ : HMTA	25 mM : 25 mM	Equimolar low-temperature solution growth
Growth	Temperature / time	90 °C / 4 h	Promotes rods while limiting bulk precipitation
Annealing	Temperature / time	300, 400, 500 °C / 1 h	Tests crystallinity–defect trade-off
XRD	Scan range	20–80° (2θ)	Confirms wurtzite phase and orientation
SEM	Rod measurements	≥50 rods / sample	Provides diameter and length distributions
Gas test	Ethanol	10–500 ppm	Concentration-response curve
Gas test	Operating temperature	150–350 °C	Locates maximum response
Electrical	Bias	1–5 V	Stable low-field resistance measurement

Results

The proposed synthesis should yield a continuous ZnO nanorod layer with the hexagonal wurtzite crystal structure and preferential growth along the c-axis. Vayssieres (2003) and Greene et al. (2005) provide precedent for oriented aqueous growth, while subsequent sensor studies show that solution-grown rods can be integrated into functioning devices. The XRD pattern is therefore expected to contain the characteristic ZnO reflections without secondary zinc hydroxide or metallic zinc phases. SEM should show rods in the approximate tens-to-low-hundreds of nanometers diameter range, with rod length determined mainly by precursor concentration and growth time. Samples annealed at 400–500 °C are expected to show sharper XRD reflections than the 300 °C sample, whereas the lower-temperature sample may retain a larger concentration of surface defects.

Optically, the absorption edge should occur near the ultraviolet region corresponding to a band gap around the bulk ZnO value, with modest variation caused by defects and nanostructure dimensions. PL should include near-band-edge ultraviolet emission together with a variable visible band associated with native and surface-related states. For sensor operation, resistance in air should stabilize before exposure, then decrease upon ethanol introduction because the reducing gas restores electrons previously trapped by chemisorbed oxygen. The response should rise with ethanol concentration and exhibit an optimum with operating temperature rather than increasing indefinitely. Comparable behavior was reported for ethanol-sensitive ZnO nanowires by Wu, Ting, and Huang (2009), while Ahn et al. (2009) demonstrated that ZnO nanowire device geometry can strongly influence response and recovery.

Table 3. Expected acceptance criteria and literature benchmarks for the proposed sensor

Output	Expected criterion for this methodology	Literature benchmark / basis
Crystal phase	Only hexagonal wurtzite ZnO peaks; no	Oriented aqueous growth

	major secondary phase	reported by Vayssieres (2003) and Greene et al. (2005)
Morphology	Dense nanorods; diameter typically <150 nm; reproducible across substrate	Nanoscale rods/wires repeatedly used for gas sensing before 2016
Optical behavior	UV absorption edge; PL showing near-band-edge plus defect-related emission	ZnO optical/sensor behavior summarized by Wei et al. (2011)
Gas response	$R_a/R_g > 1$ for ethanol; response increases with concentration over a useful range	Ethanol-sensitive ZnO nanowires demonstrated by Wu et al. (2009)
Temperature behavior	Clear optimum between about 200 and 300 °C for ethanol is plausible	Nanostructured ZnO gas sensors commonly show temperature-dependent maxima
Repeatability	Three-cycle response variation preferably <10%	Required for meaningful sensor comparison
Selectivity	Ethanol response distinguishable from at least three interferents	Needed to separate sensitivity from nonspecific conductivity changes

A successful outcome is not defined as the highest possible response alone. The optimized sample should show a balance of high response, short recovery, low drift and stable morphology. If the 500 °C sample is more crystalline but less responsive, this would suggest that surface defect removal has reduced adsorption-active sites. If the 300 °C sample responds strongly but drifts or recovers slowly, incomplete precursor removal or excessive defect density may be responsible. The 400 °C condition is therefore expected to provide a useful compromise, but the selection must be based on measured structural and sensing data. Morphology-dependent behavior reported by Rai, Kwak, and Yu (2013) supports this comparative approach rather than relying on a single condition.

The methodology can also be extended after gas testing. The same nanorod geometry may be incorporated into UV photodetectors, as demonstrated by Su et al. (2010), or surface-functionalized for biosensing, consistent with the later analyses of Tereshchenko et al. (2016) and Hahm (2016). Thus, the principal result of the methodology is a validated nanostructured ZnO platform whose material properties are sufficiently characterized to support multiple sensor-device architectures.

Conclusion and Discussion

This paper defines a practical methodology for synthesizing and characterizing ZnO nanorods for sensor devices using seeded hydrothermal growth, controlled annealing, multitechnique characterization and interdigitated-electrode testing. The method is deliberately based on established literature available through 2016. Low-temperature aqueous growth is chosen for accessibility and direct device integration; XRD

and SEM establish phase and morphology; UV-visible and PL measurements probe optical quality and defect-related states; and controlled gas exposure links these properties to chemiresistive behavior. The experimental design also treats annealing temperature, operating temperature and analyte concentration as explicit variables rather than hidden processing details. The central methodological principle is that ZnO sensor performance emerges from an interaction between surface chemistry and device architecture. High surface area increases the number of adsorption sites, but response can still be limited by poor electrical contacts, excessive agglomeration, humidity interference or unstable defects. Conversely, aggressive annealing may improve crystallinity while removing surface states that contribute to chemical sensitivity. Accordingly, the best material should be selected using a multi-criterion assessment that includes structural purity, morphology, response magnitude, response/recovery kinetics, repeatability and selectivity. The literature from Wang et al. (2006), Xu et al. (2006), Wu et al. (2009), Ahn et al. (2009), Lupan et al. (2014) and Kumar et al. (2015) collectively supports this structure-property-device perspective. A limitation of the present paper is that it is methodology-focused and does not claim original measured results. The benchmark outcomes in Section 7 are therefore decision criteria that should be replaced by actual XRD peak positions, SEM statistics, optical spectra and gas-response curves when the experiment is performed. Future work may introduce noble-metal functionalization, controlled doping, UV activation or biomolecule immobilization to reduce operating temperature and improve

selectivity. Even without these modifications, the proposed protocol provides a coherent and reproducible starting point for laboratory investigation of ZnO-based nanosensors.

References

- Vayssieres, L. (2003). Growth of arrayed nanorods and nanowires of ZnO from aqueous solutions. *Advanced Materials*, 15(5), 464–466. <https://doi.org/10.1002/adma.200390108>
- Greene, L. E., Law, M., Tan, D. H., Montano, M., Goldberger, J., Somorjai, G., & Yang, P. (2005). General route to vertical ZnO nanowire arrays using textured ZnO seeds. *Nano Letters*, 5(7), 1231–1236. <https://doi.org/10.1021/nl050788p>
- Wang, C. H., Chu, X. F., & Wu, M. W. (2006). Detection of H₂S down to ppb levels at room temperature using sensors based on ZnO nanorods. *Sensors and Actuators B: Chemical*, 113(1), 320–323. <https://doi.org/10.1016/j.snb.2005.03.011>
- Xu, J., Chen, Y., Chen, D., & Shen, J. (2006). Hydrothermal synthesis and gas sensing characters of ZnO nanorods. *Sensors and Actuators B: Chemical*, 113(1), 526–531. <https://doi.org/10.1016/j.snb.2005.03.097>
- Wu, W.-Y., Ting, J.-M., & Huang, P.-J. (2009). Electrospun ZnO nanowires as gas sensors for ethanol detection. *Nanoscale Research Letters*, 4, 513–517. <https://doi.org/10.1007/s11671-009-9271-4>
- Ahn, M.-W., Park, K.-S., Heo, J.-H., Kim, D.-W., Choi, K. J., & Park, J.-G. (2009). On-chip fabrication of ZnO-nanowire gas sensor with high gas sensitivity. *Sensors and Actuators B: Chemical*, 138(1), 168–173. <https://doi.org/10.1016/j.snb.2009.02.008>
- Su, Y. K., Peng, S. M., Ji, L. W., Wu, C. Z., Cheng, W. B., & Liu, C. H. (2010). Ultraviolet ZnO nanorod photosensors. *Langmuir*, 26(1), 603–606. <https://doi.org/10.1021/la902171j>
- Wei, A., Pan, L., & Huang, W. (2011). Recent progress in the ZnO nanostructure-based sensors. *Materials Science and Engineering: B*, 176(18), 1409–1421. <https://doi.org/10.1016/j.mseb.2011.09.005>
- Rai, P., Kwak, W.-K., & Yu, Y.-T. (2013). Solvothermal synthesis of ZnO nanostructures and their morphology-dependent gas-sensing properties. *ACS Applied Materials & Interfaces*, 5(8), 3026–3032. <https://doi.org/10.1021/am302811h>
- Lupan, O., Pauporte, T., & Chow, L. (2014). Synthesis and gas sensor applications of nanostructured ZnO grown at low temperatures. *Turkish Journal of Physics*, 38(3), 399–419. <https://doi.org/10.3906/fiz-1406-21>
- Kumar, R., Al-Dossary, O., Kumar, G., & Umar, A. (2015). Zinc oxide nanostructures for NO₂ gas-sensor applications: A review. *Nano-Micro Letters*, 7, 97–120. <https://doi.org/10.1007/s40820-014-0023-3>
- Tereshchenko, A., Bechelany, M., Viter, R., Khranovskyy, V., Smyntyna, V., Starodub, N., & Yakimova, R. (2016). Optical biosensors based on ZnO nanostructures: Advantages and perspectives. A review. *Sensors and Actuators B: Chemical*, 229, 664–677. <https://doi.org/10.1016/j.snb.2016.01.099>
- Hahm, J.-I. (2016). Fundamental properties of one-dimensional zinc oxide nanomaterials and implementations in various detection modes of enhanced biosensing. *Annual Review of Physical Chemistry*, 67, 691–717. <https://doi.org/10.1146/annurev-physchem-031215-010949>