



Optical and Structural Characterization of Rare Earth Doped Phosphor Materials

¹Leocadia Belhocine

¹Department of Computer Science and Engineering, Kelana Technical and Management College, Malaysia

¹leocadia.belhocine@ktmc-my.net

Peer Review Information

Submission: 11 Oct 2016

Revision: 26 Nov 2016

Acceptance: 26 Dec 2026

Keywords

rare-earth phosphor,
photoluminescence, X-ray
diffraction, europium,
dysprosium

Abstract

Rare-earth-doped phosphors are functional inorganic materials whose optical response is controlled jointly by the crystal structure of the host, the oxidation state and site symmetry of the activator, dopant concentration, defects, and thermal history. This methodology paper presents a compact and reproducible protocol for correlating structural characteristics with optical performance in oxide phosphors, using europium- and dysprosium-activated strontium aluminate as a representative system while retaining applicability to yttria, borate, molybdate, phosphate, and titanate hosts. The proposed procedure combines controlled powder synthesis with X-ray diffraction (XRD), scanning electron microscopy/energy-dispersive spectroscopy (SEM/EDS), Fourier-transform infrared spectroscopy (FTIR), UV-visible spectroscopy, photoluminescence excitation/emission (PLE/PL), decay analysis, and CIE chromaticity calculations. XRD establishes phase purity, lattice response, and crystallite size; microscopy verifies particle morphology and dopant distribution; spectroscopic measurements identify host absorption and characteristic 4f-4f or 4f-5d transitions. Literature up to 2016 shows that improved crystallinity can enhance Eu^{3+} emission, Dy^{3+} commonly produces blue-yellow emission, and $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+}, \text{Dy}^{3+}$ exhibits broad green emission with persistent luminescence. The methodology emphasizes concentration-series measurements and explicit identification of concentration quenching rather than reporting a single composition. Representative outcomes are stated as literature-consistent expectations and are not presented as newly measured data. The framework is suitable for laboratories seeking a concise protocol for phosphor screening, structure-property analysis, and optimization for lighting, display, sensing, or persistent-luminescence applications.

Introduction

Phosphors are host lattices containing a small fraction of optically active ions that absorb energy and re-emit it at characteristic wavelengths. Rare-earth ions are particularly valuable because their partially filled 4f shell produces sharp, element-specific transitions, while divalent ions such as Eu^{2+} can also show broad $4f^65d^1 \rightarrow 4f^7$ emission that is strongly

sensitive to the host crystal field. The theoretical basis for interpreting trivalent rare-earth spectra was established by Judd (1962) and Ofelt (1962), whose intensity framework links transition probabilities to local symmetry and ligand environment. Consequently, optical characterization is incomplete without parallel structural characterization of the host lattice.

A practical phosphor-development study therefore requires three linked questions: whether the intended host phase has formed; whether the activator has been incorporated without creating dominant impurity phases; and whether the resulting excitation, emission, and decay behavior is favorable at a realistic dopant concentration. Persistent alkaline-earth aluminates illustrate this interdependence. Hölsä et al. (2001) showed that Eu^{2+} provides the principal blue/green emitting center in MAl_2O_4 hosts and that selected trivalent rare-earth co-dopants can strongly modify afterglow behavior. This paper defines a step-by-step methodology for obtaining the structural and optical evidence needed to answer these questions within one coherent experimental design.

Literature Review

The literature up to 2016 demonstrates that synthesis route, host chemistry, activator valence, and heat treatment all influence phosphor performance. In persistent strontium aluminate, Peng et al. (2004a) prepared nanoscale $\text{SrAl}_2\text{O}_4:\text{Eu},\text{Dy}$ by solution combustion and reported broad green emission near 513 nm, while their sol-gel study produced a related emission band near 506 nm and demonstrated that a single phase could be obtained at a lower processing temperature than conventional solid-state routes (Peng et al., 2004b). These studies established combustion and sol-gel processing as useful alternatives when finer particle sizes and improved chemical homogeneity are required.

Host structure can be as important as activator chemistry. Eu^{3+} -doped cubic Y_2O_3 is a standard red phosphor because Eu^{3+} occupies crystallographic sites that support strong $^5\text{D}_0 \rightarrow ^7\text{F}_J$ emission. Packiyaraj and Thangadurai (2014) found that $\text{Y}_2\text{O}_3:\text{Eu}^{3+}$ nanoparticles annealed at higher temperature showed greater crystallinity and stronger red photoluminescence, illustrating why XRD peak development and thermal treatment should be correlated with PL intensity rather than discussed independently. In $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+},\text{Dy}^{3+}$,

Kshatri and Khare (2014) used XRD, SEM, and EDX together with PL and afterglow measurements and reported a strong emission near 515 nm. The study is especially relevant methodologically because it integrates composition, structure, morphology, and luminescence within one sample series.

Trivalent dysprosium provides a complementary model for line-emitting phosphors. Kharabe et al. (2015) reported blue and yellow emissions from Dy^{3+} -activated LiCaBO_3 and a red Eu^{3+} band near 614 nm in the corresponding Eu^{3+} series. Dutta et al. (2015) showed that $\text{Dy}^{3+}/\text{K}^{+}$ -doped CaMoO_4 could be assessed by XRD, TEM, FTIR, excitation spectroscopy, decay analysis, and quantum-yield calculations, confirming the value of multimethod characterization for assessing both crystal phase and radiative behavior. Vidyadharan et al. (2016) similarly used XRD and Judd-Ofelt analysis to study Dy^{3+} in $\text{Sr}_{0.5}\text{Ca}_{0.5}\text{TiO}_3$ and observed characteristic emissions around 481, 574, and 638 nm, while also showing that lifetime changes with dopant concentration.

The 2016 study of Wako et al. extended structure-luminescence analysis to $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+},\text{Dy}^{3+},\text{Nd}^{3+}$ thin films, demonstrating that substrate temperature and argon pressure can shift XRD peaks and alter PL intensity through changes in crystal field and microstructure. Beyond lighting, rare-earth-doped phosphors can also act as spectral converters; Lian et al. (2013) reviewed downshifting, downconversion, and upconversion routes for reducing spectral mismatch in photovoltaic devices. Taken together, the pre-2017 literature supports a methodology in which (i) phase identity is verified first, (ii) morphology and composition are checked, (iii) excitation and emission are mapped across a concentration series, and (iv) lifetime, color coordinates, and quenching behavior are used to determine the optimum formulation rather than selecting it from emission intensity alone.

Table 1. Representative literature used to define the characterization strategy

Study	Host / dopant	Key methods	Methodological relevance
Peng et al. (2004a)	$\text{SrAl}_2\text{O}_4:\text{Eu},\text{Dy}$	Combustion, TEM, PL	Nanoscale synthesis; broad Eu^{2+} emission
Packiyaraj & Thangadurai (2014)	$\text{Y}_2\text{O}_3:\text{Eu}^{3+}$	XRD, TEM, PL, lifetime	Annealing/crystallinity-PL correlation

Kshatri & Khare (2014)	$\text{SrAl}_2\text{O}_4:\text{Eu}^{2+}, \text{Dy}^{3+}$	XRD, SEM/EDS, PL, decay	Integrated structural and optical analysis
Dutta et al. (2015)	$\text{CaMoO}_4:\text{Dy}^{3+}, \text{K}^+$	XRD, TEM, FTIR, PL, decay	Spectral parameters and quantum-yield approach
Vidyadharan et al. (2016)	$\text{Sr}_{0.5}\text{Ca}_{0.5}\text{TiO}_3:\text{Dy}^{3+}$	XRD, PL, JO analysis, CIE	Concentration/lifetime and color analysis

Methodology

1. Experimental Design and Sample Series

A concentration-series design is recommended because luminescence may initially increase with activator content and then decrease through non-radiative energy migration or concentration quenching. As a representative system, prepare $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+}, \text{Dy}^{3+}$ powders with Eu fixed at approximately 1 mol% and Dy varied at 0, 0.5, 1.0, and 1.5 mol% relative to the Sr site. The exact series may be adapted to another host such as $\text{Y}_2\text{O}_3:\text{Eu}^{3+}$ or $\text{CaMoO}_4:\text{Dy}^{3+}$, but all compositions must be synthesized under identical batch size, thermal schedule, and atmosphere. Include an undoped host or host-only reference whenever the host has appreciable intrinsic emission.

2. Raw Materials and Synthesis

Use analytical-grade $\text{Sr}(\text{NO}_3)_2$, $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$, $\text{Eu}(\text{NO}_3)_3 \cdot 5\text{H}_2\text{O}$, $\text{Dy}(\text{NO}_3)_3$ (or nitrate solutions prepared from the corresponding oxides), and urea as fuel for solution combustion. Calculate the oxidizer-to-fuel ratio from total nitrate oxidizing valence so that all samples have the same nominal fuel balance. Dissolve the salts in deionized water, combine under continuous stirring, and adjust only the minimum solution volume required for homogeneous mixing. Heat the precursor in a preheated furnace at about 500–600 °C until spontaneous combustion produces a porous powder. Lightly grind the ash and then calcine at approximately 1000–1100 °C. For Eu^{2+} -containing SrAl_2O_4 , carry out the final heat treatment in a weak reducing atmosphere, because Eu^{3+} must be reduced to the optically active Eu^{2+} state. This workflow follows the logic of combustion and sol-gel routes reported for $\text{SrAl}_2\text{O}_4:\text{Eu}, \text{Dy}$ by Peng et al. (2004a, 2004b) and is consistent with later combustion-based structural/optical studies (Kshatri & Khare, 2014).

3. Structural Characterization

Record powder XRD patterns over $2\theta \approx 10\text{--}80^\circ$ using Cu K α radiation. Identify the host phase by comparison with an appropriate reference diffraction file, and inspect every sample for

impurity peaks. Determine the strongest peak position, full width at half maximum (FWHM), and relative intensity using the same background and peak-fitting procedure for all compositions. Estimate the apparent crystallite size from $D = K\lambda/(\beta \cos\theta)$, where β is the instrument-corrected FWHM in radians. Report the equation as an estimate rather than a direct particle-size measurement. If sufficient peaks are available, lattice parameters may be refined and compared across the dopant series to evaluate substitution-induced strain. The XRD interpretation should explicitly distinguish phase formation from crystallinity improvement, an important point demonstrated in $\text{Y}_2\text{O}_3:\text{Eu}^{3+}$ after annealing (Packiyaraj & Thangadurai, 2014).

4. Morphology, Composition, and Bonding

Examine powder morphology by SEM at at least three non-overlapping fields and two magnifications. Report agglomeration, grain shape, approximate particle-size range, and porosity qualitatively unless statistically adequate image analysis is performed. Use EDS to verify Sr, Al, O, Eu, and Dy and to exclude major foreign elements; EDS should be treated as semi-quantitative for low dopant levels. Record FTIR spectra in the mid-infrared region to confirm characteristic metal-oxygen lattice vibrations and to detect residual nitrate, carbonate, hydroxyl, or organic species. Dutta et al. (2015) provides a useful precedent for combining XRD, microscopy, FTIR, and luminescence in rare-earth-doped oxide phosphors.

5. Optical Characterization and Data Analysis

Collect diffuse-reflectance UV-visible spectra from approximately 200–800 nm using the same sample packing thickness. Convert reflectance to the Kubelka-Munk function when an optical band-edge estimate is required. For luminescence, first record a PLE spectrum while monitoring the dominant emission; then select one or more excitation wavelengths within the strongest absorption/excitation region and record PL spectra over the visible range. Correct spectra for instrument response if quantitative

comparison is intended. Normalize only when comparing spectral shape; use unnormalized integrated intensity when comparing performance among dopant concentrations. For Eu^{2+} hosts, expect broad host-sensitive $4f^65d^1 \rightarrow 4f^7$ emission, whereas Eu^{3+} and Dy^{3+} generally show sharper intra-4f lines. The distinction follows the spectroscopic principles summarized by Judd (1962) and Ofelt (1962) and is observed experimentally across Eu^{3+} , Dy^{3+} , and Eu^{2+} phosphors in the selected literature.

Measure decay curves at the principal emission wavelength after pulsed or shuttered excitation. Fit the simplest model that describes the data

adequately: a single exponential for a nearly uniform emitting environment, a bi-exponential or stretched model only when justified by residuals and physical reasoning. Calculate CIE x,y coordinates from the corrected emission spectrum and, when appropriate, correlated color temperature or yellow-to-blue intensity ratio. Concentration quenching is identified when integrated PL intensity decreases above an optimum dopant level while phase purity remains essentially unchanged. Kharabe et al. (2015) and Vidyadharan et al. (2016) show why concentration-dependent intensity and lifetime should be interpreted together rather than independently.




Figure 1. Step-by-step synthesis and characterization workflow for rare-earth-doped phosphor powders.

Table 2. Measurements and minimum reporting outputs

Technique	Primary output	Minimum comparison across series
XRD	Phase, peak position, FWHM, crystallite-size estimate	Same scan range and fit settings
SEM/EDS	Morphology and elemental verification	Same magnification plus several fields
FTIR	Lattice/impurity vibrations	Same baseline correction
UV-Vis/DRS	Absorption edge / excitation window	Same packing and reference
PLE/PL	Excitation bands, emission peaks, integrated intensity	Same slit widths, power, detector settings
Decay/CIE	Lifetime and color coordinates	Same excitation/emission conditions

Results

Because this paper specifies a methodology and does not claim a new experimental campaign, the outcomes below are representative, literature-consistent results that the proposed protocol is designed to test. For a successfully prepared $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+},\text{Dy}^{3+}$ series, XRD should primarily match monoclinic SrAl_2O_4 , with stronger and narrower reflections after adequate calcination

indicating increased crystallinity. Wako et al. (2016) reported systematic changes in peak position and width with processing conditions in $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+},\text{Dy}^{3+},\text{Nd}^{3+}$ films, showing that small structural changes can accompany optical changes even when the nominal host remains the same. If additional peaks appear, they should be assigned before any PL enhancement is attributed to dopant optimization.

SEM is expected to show agglomerated combustion-derived particles with a porous or irregular morphology, while EDS should confirm the host elements and rare-earth dopants without strong contamination. Morphology is not expected to equal XRD crystallite size because one SEM particle may contain many coherent crystallites. For $\text{Y}_2\text{O}_3:\text{Eu}^{3+}$, Packiyaraj and Thangadurai (2014) found that higher-temperature annealing increased particle/crystallite dimensions and strengthened red emission; this is the type of structure-property correlation that should be sought rather than treating each instrument independently.

Optically, $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+},\text{Dy}^{3+}$ should show a broad green band associated with $\text{Eu}^{2+} 5d \rightarrow 4f$ emission. Values around 506–520 nm have been reported in closely related samples (Hölsä et al., 2001; Peng et al., 2004a, 2004b; Kshatri & Khare, 2014). Dy^{3+} in other oxide/borate hosts is expected to produce characteristic blue and yellow lines, including transitions around 480–490 and 570–580 nm, as observed by Kharabe et al. (2015) and Vidyadharan et al. (2016). Eu^{3+} -activated materials generally exhibit a dominant red $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transition near 610–615 nm when Eu^{3+} occupies a non-centrosymmetric environment, consistent with the Eu^{3+} results reported for Y_2O_3 and LiCaBO_3 phosphors.




Figure 2. Illustrative concentration-dependent PL trend used to interpret an optimum dopant level. Curves are schematic and are not experimental data.

Table 3. Expected interpretation criteria for a concentration series

Observation	Interpretation	Required check
PL rises with initial dopant addition	More emitting centers / improved energy transfer	Phase purity unchanged
PL falls above optimum concentration	Possible concentration quenching	Check lifetime and impurity peaks
XRD peaks narrow after calcination	Higher crystallinity / larger coherent domains	Instrument broadening corrected
Emission peak shifts slightly	Crystal-field or site-environment change	Repeat under identical settings
Afterglow strengthened by Dy^{3+}	Trap population altered	Measure decay/TL if available

Conclusion and Discussion

The proposed methodology provides a compact route for determining how rare-earth incorporation changes the structure and optical response of phosphor materials. Its central principle is correlation: a high emission intensity is meaningful only when phase purity, dopant incorporation, thermal history, morphology, and measurement conditions are documented. XRD

should be used to confirm the host and quantify peak changes; SEM/EDS and FTIR should test morphology, elemental composition, and chemical cleanliness; and PLE/PL, decay, and CIE analyses should establish the practical optical response. The approach is deliberately concentration-based because the optimum rare-earth level is system-specific and can be limited by concentration quenching. The literature up to

2016 supports several general conclusions. First, improved crystallinity can strengthen emission, as demonstrated for $\text{Y}_2\text{O}_3:\text{Eu}^{3+}$ (Packiyaraj & Thangadurai, 2014). Second, Eu^{2+} emission is highly host-sensitive and broad, making $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+}$ particularly suitable for green persistent luminescence; Dy^{3+} can modify trapping and afterglow behavior in this host (Hölsä et al., 2001; Kshatri & Khare, 2014). Third, trivalent ions such as Dy^{3+} and Eu^{3+} retain characteristic line emissions that are valuable for interpreting local symmetry and color output (Kharabe et al., 2015; Vidyadharan et al., 2016). Finally, processing conditions can alter the crystal field and luminescence even without changing the nominal chemical formula, as shown in the thin-film study of Wako et al. (2016). These observations justify a methodology that holds synthesis conditions constant while varying only one main factor at a time. For future experimental use, the protocol can be strengthened by adding Rietveld refinement, Raman spectroscopy, absolute photoluminescence quantum yield, temperature-dependent PL, and thermoluminescence where equipment is available. If the objective is photovoltaic spectral conversion, upconversion or downconversion measurements may also be added, consistent with the application framework reviewed by Lian et al. (2013). The current methodology, however, is sufficient for a six-to-seven-page laboratory study focused specifically on optical and structural characterization and can be adapted to Eu-, Dy-, Tb-, Sm-, Er-, or Nd-doped oxide phosphors without changing its core logic.

Step-by-Step Experimental Sequence

1. Define host, activator, and 3–4 dopant concentrations plus a reference sample.
2. Weigh precursors stoichiometrically and synthesize all compositions in one controlled batch series.
3. Grind, calcine, and—when Eu^{2+} is required—apply a controlled reducing treatment.
4. Run XRD first; reject or separately discuss samples containing major impurity phases.
5. Record SEM/EDS and FTIR to verify morphology, composition, and residual chemical species.
6. Measure UV-Vis/DRS, PLE, PL, decay, and CIE coordinates under identical instrumental settings.
7. Compare integrated intensity, lifetime, peak position, and XRD characteristics to determine the optimum composition and identify quenching.

References

- Judd, B. R. (1962). Optical absorption intensities of rare-earth ions. *Physical Review*, 127(3), 750–761. <https://doi.org/10.1103/PhysRev.127.750>
- Ofelt, G. S. (1962). Intensities of crystal spectra of rare-earth ions. *The Journal of Chemical Physics*, 37(3), 511–520. <https://doi.org/10.1063/1.1701366>
- Hölsä, J., Jungner, H., Lastusaari, M., & Niittykoski, J. (2001). Persistent luminescence of Eu^{2+} doped alkaline earth aluminates, $\text{MAl}_2\text{O}_4:\text{Eu}^{2+}$. *Journal of Alloys and Compounds*, 323–324, 326–330. [https://doi.org/10.1016/S0925-8388\(01\)01084-2](https://doi.org/10.1016/S0925-8388(01)01084-2)
- Peng, T., Yang, H., Pu, X., Hu, B., Jiang, Z., & Yan, C. (2004a). Combustion synthesis and photoluminescence of $\text{SrAl}_2\text{O}_4:\text{Eu,Dy}$ phosphor nanoparticles. *Materials Letters*, 58(3–4), 352–356. [https://doi.org/10.1016/S0167-577X\(03\)00499-3](https://doi.org/10.1016/S0167-577X(03)00499-3)
- Peng, T., Liu, H., Yang, H., & Yan, C. (2004b). Synthesis of $\text{SrAl}_2\text{O}_4:\text{Eu,Dy}$ phosphor nanometer powders by sol-gel processes and its optical properties. *Materials Chemistry and Physics*, 85(1), 68–72. <https://doi.org/10.1016/j.matchemphys.2003.12.001>
- Lian, H., Hou, Z., Shang, M., Geng, D., Zhang, Y., & Lin, J. (2013). Rare earth ions doped phosphors for improving efficiencies of solar cells. *Energy*, 57, 270–283. <https://doi.org/10.1016/j.energy.2013.05.019>
- Packiyaraj, P., & Thangadurai, P. (2014). Structural and photoluminescence studies of Eu^{3+} doped cubic Y_2O_3 nanophosphors. *Journal of Luminescence*, 145, 997–1003. <https://doi.org/10.1016/j.jlumin.2013.07.074>
- Kshatri, D. S., & Khare, A. (2014). Characterization and optical properties of Dy^{3+} doped nanocrystalline $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+}$ phosphor. *Journal of Alloys and Compounds*, 588, 488–495. <https://doi.org/10.1016/j.jallcom.2013.11.045>
- Kharabe, V. R., Oza, A. H., & Dhoble, S. J. (2015). Synthesis, PL characterizations and concentration quenching effect in Dy^{3+} and Eu^{3+} activated LiCaBO_3 phosphor. *Luminescence*, 30(4), 432–438. <https://doi.org/10.1002/bio.2756>
- Dutta, S., Som, S., & Sharma, S. K. (2015). Excitation spectra and luminescence decay analysis of K^{3+} compensated Dy^{3+} doped CaMoO_4

phosphors. RSC Advances, 5, 7380–7387.
<https://doi.org/10.1039/C4RA12447B>

Vidyadharan, V., Sreeja, E., Jose, S. K., Joseph, C., Unnikrishnan, N. V., & Biju, P. R. (2016). Spectroscopic and photoluminescence characterization of Dy^{3+} in $\text{Sr}_{0.5}\text{Ca}_{0.5}\text{TiO}_3$ phosphor. Luminescence, 31(1), 202–209.
<https://doi.org/10.1002/bio.2946>

Wako, A. H., Dejene, F. B., & Swart, H. C. (2016). Structural and luminescence properties of $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+},\text{Dy}^{3+},\text{Nd}^{3+}$ phosphor thin films grown by pulsed laser deposition. Physica B: Condensed Matter, 480, 116–124.
<https://doi.org/10.1016/j.physb.2015.09.049>