



Computational Study of Electronic Band Structures in Graphene-Based Nanomaterials

¹Deepansh Leroux-Martin

¹Department of Computer Science and Engineering, Peninsula Institute of Engineering Studies, Malaysia

¹deepansh.leroux.martin@pies-my.edu

Peer Review Information

Submission: 08 April 2017

Revision: 13 May 2017

Acceptance: 29 May 2017

Keywords

Graphene. electronic band structure. density functional theory. graphene nanoribbons. tight-binding model

Abstract

Graphene-based nanomaterials are attractive for nanoelectronic, optoelectronic, sensing, and thermoelectric applications because their electronic states can be modified by lateral confinement, edge geometry, chemical substitution, strain, and structural defects. This methodology paper presents a reproducible computational framework for examining electronic band structures in pristine graphene and graphene-derived nanostructures using a two-level strategy: a nearest-neighbor tight-binding model for rapid physical validation and density functional theory (DFT) for atomistic refinement. The workflow defines structural model construction, vacuum separation, geometry optimization, Brillouin-zone sampling, band-path calculations, density-of-states analysis, and convergence criteria. A tight-binding calculation carried out for pristine graphene reproduces the characteristic crossing of valence and conduction bands at the K point, giving a zero-band gap in the ideal sheet. The interpretation of nanoribbon, doped, strained, and defected systems is then benchmarked against peer-reviewed studies published no later than 2017. The literature demonstrates that lateral confinement and edge effects can open band gaps in graphene nanoribbons, while B/N substitution, strain, and defects shift or reshape states near the Fermi level. The proposed protocol therefore provides a compact and defensible route for comparing electronic-structure changes across graphene-based nanomaterials while preserving computational efficiency and methodological transparency.

Introduction

The isolation of atomically thin graphitic carbon established graphene as a practical two-dimensional electronic material and revealed an unusual semimetallic electronic response with ambipolar carrier transport (Novoselov et al., 2004). Its honeycomb lattice contains two carbon sublattices and produces low-energy quasiparticles whose dispersion is approximately linear near the inequivalent K and K' points. This Dirac-like spectrum is central to graphene physics and explains why pristine monolayer graphene has no conventional band gap despite its exceptional carrier mobility (Geim & Novoselov, 2007; Castro Neto et al., 2009).

A zero-band gap is scientifically important but technologically restrictive for digital switching, where a finite energy separation between occupied and unoccupied states is normally required. Graphene-based nanomaterials offer several routes to overcome this limitation. Reducing a graphene sheet to a narrow ribbon quantizes transverse electronic motion, and the resulting spectrum depends strongly on ribbon width and whether the edges are armchair or zigzag. Early tight-binding calculations identified localized states at zigzag edges (Nakada et al., 1996), while first-principles calculations later showed that both armchair and zigzag

nanoribbons can acquire finite gaps through confinement, edge chemistry, and spin polarization (Son et al., 2006). Systematic DFT calculations also demonstrated an inverse relationship between ribbon width and achievable band gap and emphasized the effect of edge termination and crystallographic orientation (Barone et al., 2006).

Electronic structure can also be engineered without physically narrowing the sheet. Substitutional boron and nitrogen change carrier concentration and the position of electronic states relative to the Fermi energy (Panchakarla et al., 2009). Elastic deformation modifies hopping amplitudes and can produce strong anisotropy or, at sufficiently large strain, alter the gap topology (Pereira et al., 2009). Vacancies, reconstructed bonds, adsorbates, and line defects break ideal translational symmetry and can generate localized states, magnetism, or gap opening (Banhart et al., 2011; Guerra et al., 2016). These effects motivate a unified computational procedure in which pristine graphene is used as a calibration system and progressively more complex nanostructures are analyzed with the same convergence standards and electronic descriptors.

The objective of this paper is therefore to establish a step-by-step methodology for studying the band structures of graphene-based nanomaterials and to demonstrate the physical validity of the approach with a calculated pristine-graphene band diagram. References are restricted to publications from 2017 or earlier, as requested, so the framework reflects the established computational literature available through that period.

Literature Review

The theoretical understanding of graphene began from the bipartite honeycomb lattice and the existence of special edge states. Nakada et al. (1996) used a tight-binding description of finite graphite ribbons and showed that zigzag boundaries support nearly flat electronic bands around the Fermi level, whereas armchair edges do not host equivalent localized states. This work provided an early computational explanation for the strong sensitivity of nanoscale graphene to edge shape.

After graphene became experimentally accessible, first-principles studies focused on whether quantum confinement could produce semiconductor-like gaps. Son et al. (2006) calculated hydrogen-passivated armchair and zigzag graphene nanoribbons and found finite energy gaps in both families. Their results

showed that armchair gaps arise from confinement together with edge effects, while zigzag gaps are tied to edge magnetization and sublattice asymmetry. Barone et al. (2006) independently studied ribbons of different widths and orientations using DFT and concluded that narrow armchair ribbons can possess technologically useful gaps, with the gap generally decreasing as width increases.

The broader electronic physics was consolidated by Castro Neto et al. (2009), who reviewed the Dirac spectrum, multilayer effects, disorder, interactions, and edge-state behavior. In the same period, approaches for intentional band engineering expanded. Panchakarla et al. (2009) combined experiment and first-principles theory to demonstrate systematic modification of the electronic structure through B and N doping. Pereira et al. (2009) used a tight-binding treatment of uniaxial strain and showed that the Dirac spectrum is robust under moderate deformation, although substantial anisotropy and gap formation can occur when deformation becomes sufficiently large.

Defects emerged as another design variable rather than only a source of degradation. Banhart et al. (2011) reviewed vacancies, reconstructions, line defects, and foreign atoms and explained that imperfections can tailor local electronic properties. Guerra et al. (2016) used first-principles calculations to show that point and line defects can drive graphene between semimetallic, metallic, and semiconducting behavior. Moon et al. (2016) further demonstrated that edge chemistry in zigzag nanoribbons can change band gaps substantially; non-aromatic ketone, ether, and graphitic configurations altered the bands near the Fermi level more strongly than carboxyl, hydroxyl, pyridinic, or pyrrolic groups.

By 2017, DFT had become a standard element of multiscale graphene-nanoribbon studies. Li and Grossman (2017) used VASP with projector-augmented-wave potentials and the PBE functional to calculate atomic structures, density of states, and band structures before linking the electronic information to transport analysis. This progression—from tight-binding physics to converged first-principles calculations—supports the hybrid methodology used here: tight binding is retained for rapid verification of the Dirac crossing, while DFT is specified for quantitative comparisons among realistic nanomaterial structures.

Methodology

Step 1 - Define the structural models. Pristine graphene is represented by a two-atom primitive cell with an in-plane lattice constant close to 2.46 Å. Graphene nanoribbons are generated by cutting the sheet along armchair or zigzag directions and saturating dangling carbon bonds with hydrogen when passivated edges are required. Doped models are created by replacing selected C atoms with B or N, whereas defective models are formed by removing atoms or introducing reconstructed bonds. A vacuum layer of at least 15 Å is placed normal to the sheet, and comparable vacuum is used transverse to one-dimensional ribbons to suppress artificial periodic-image interactions.

Step 2 - Perform an initial tight-binding validation. For pristine graphene, only the carbon pz orbitals are retained and nearest-neighbor hopping is described by $t = 2.70$ eV. The two-band dispersion is obtained from $E_{\pm}(k) = \pm t[1 + \exp(ik \cdot a_1) + \exp(ik \cdot a_2)]$, where a_1 and a_2 are the primitive lattice vectors. The band energies are sampled along Γ -M-K- Γ . The purpose of this calculation is not to replace DFT but to verify that the structural and reciprocal-space definitions reproduce the expected zero-gap crossing at K, consistent with the established graphene spectrum (Castro Neto et al., 2009).

Step 3 - Set up DFT calculations. For quantitative calculations, the Kohn-Sham equations are solved using a plane-wave code such as VASP. The PBE generalized-gradient approximation is selected for exchange and correlation (Perdew et al., 1996), and carbon, hydrogen, boron, and nitrogen ion-electron interactions are represented with projector-augmented-wave potentials (Kresse & Joubert, 1999). Efficient iterative plane-wave minimization follows the VASP methodology described by Kresse and Furthmüller (1996).

Step 4 - Converge basis and k-point sampling. A plane-wave cutoff near 500 eV is a practical starting point and should be increased until total-energy changes fall below about 1 meV per atom. Brillouin-zone integration uses Monkhorst-Pack

meshes (Monkhorst & Pack, 1976). A dense two-dimensional mesh such as $21 \times 21 \times 1$ is appropriate for the primitive graphene sheet, whereas a ribbon may use approximately $1 \times 1 \times 21$ points along its periodic axis. Each production calculation should be preceded by explicit cutoff and k-point convergence tests.

Step 5 - Optimize the geometry. Atomic positions are relaxed until residual forces are below 0.01 eV Å⁻¹ and the electronic self-consistency cycle reaches about 10⁻⁶ eV. For pristine graphene the in-plane lattice may be optimized; for comparative defect or dopant studies it is often preferable to keep the supercell dimensions fixed after obtaining the reference lattice and relax internal coordinates only. Spin-polarized calculations are required for zigzag nanoribbons and defect configurations that may support magnetic states (Son et al., 2006; Guerra et al., 2016).

Step 6 - Calculate bands and density of states. After relaxation, a self-consistent charge density is obtained using the converged mesh. A non-self-consistent band calculation is then performed along high-symmetry paths. For the primitive sheet the path Γ -M-K- Γ is used; for nanoribbons the one-dimensional Brillouin zone is sampled from Γ to the zone boundary. The band gap E_g is extracted as ECBM – EVBM. Total and projected density of states are calculated to identify whether new states originate from carbon edge atoms, dopants, defects, or adsorbates.

Step 7 - Analyze band engineering. Four comparisons are recommended: (i) pristine sheet versus confined ribbon, (ii) armchair versus zigzag edge, (iii) pristine versus B/N substituted structures, and (iv) pristine versus strained or defective structures. Changes are quantified through band gap, Fermi-level shift, band-edge position, spin splitting, and localization of projected states. The direction and magnitude of these changes are compared with established results on confinement (Son et al., 2006; Barone et al., 2006), chemical doping (Panchakarla et al., 2009), strain (Pereira et al., 2009), and edge/defect modification (Banhart et al., 2011; Moon et al., 2016).

Table 1. Recommended computational parameters for the electronic-structure workflow

Parameter	Pristine graphene	Graphene nanoribbon / supercell
Electronic model	NN tight binding + DFT	Spin-polarized DFT where required
Exchange-correlation	PBE-GGA	PBE-GGA
Plane-wave cutoff	~500 eV; convergence tested	~500 eV; convergence tested

k-point mesh	$\sim 21 \times 21 \times 1$	$\sim 1 \times 1 \times 21$ along periodic direction
Vacuum spacing	$\geq 15 \text{ \AA}$ out of plane	$\geq 15 \text{ \AA}$ in nonperiodic directions
Force criterion	$< 0.01 \text{ eV \AA}^{-1}$	$< 0.01 \text{ eV \AA}^{-1}$
Electronic tolerance	$\sim 10^{-6} \text{ eV}$	$\sim 10^{-6} \text{ eV}$
Primary outputs	Band structure, DOS, Fermi level	Band gap, PDOS, spin/edge states

Results

The tight-binding validation reproduces the defining electronic feature of pristine graphene. Along the Γ -M-K- Γ path, the valence and conduction branches meet at the K point without an intervening gap (Figure 1). In the nearest-neighbor model used here, the numerical band gap is 0.000 eV to the resolution of the calculation. The calculated dispersion is approximately linear close to K, which is the expected Dirac-cone behavior described in the graphene literature (Geim & Novoselov, 2007; Castro Neto et al., 2009). This result is an important methodological check because an incorrect lattice convention, reciprocal path, or hopping connectivity can incorrectly remove the K-point crossing.




Figure 1. Calculated nearest-neighbor tight-binding band structure of pristine graphene. The valence and conduction bands touch at K, giving the ideal sheet a zero-band gap.

For graphene nanomaterials, the same zero-gap behavior is not generally preserved. Hydrogen-passivated armchair ribbons are expected to be semiconducting, with gaps that depend systematically on width and family index, while zigzag ribbons require spin-polarized treatment because their edge states can become magnetic (Son et al., 2006; Barone et al., 2006). The benchmark literature therefore provides clear acceptance criteria for DFT calculations: ribbon band gaps should decrease overall as width increases, and zigzag-edge states should appear strongly near the Fermi energy unless passivation, defects, or symmetry breaking modify them.

Chemical and structural modifications offer additional signatures. B/N substitution changes carrier concentration and shifts the electronic structure around the Fermi level (Panchakarla et al., 2009). Defects can transform the sheet from semimetallic behavior to metallic or semiconducting behavior depending on topology (Guerra et al., 2016). Edge chemistry can also produce sizable band changes: Moon et al. (2016) reported calculated gaps of approximately 0.606 eV and 0.641 eV for ketone- and ether-modified zigzag ribbons, respectively, while several nitrogen edge configurations produced gaps around 0.29-0.42 eV. These literature values are not presented as new calculations here; they are comparison targets for validating the proposed workflow.

Table 2. Benchmark electronic-structure trends for interpreting calculated graphene nanomaterials

System	Expected band feature	Key variable	Benchmark source
Pristine graphene	Zero-gap crossing at K	Ideal sp^2 lattice	This TB calculation; Castro Neto et al. (2009)
Armchair GNR	Finite, width-dependent gap	Ribbon width / family	Son et al. (2006); Barone et al. (2006)
Zigzag GNR	Edge states; spin-dependent gap	Edge magnetism	Nakada et al. (1996); Son et al. (2006)
B/N-doped graphene	Fermi-level and carrier-type shift	Dopant identity / site	Panchakarla et al. (2009)
Defective graphene/GNR	Localized states; gap/metallicity changes	Defect type / position	Banhart et al. (2011); Guerra et al. (2016)

Functionalized ZGNR	Gap depends on edge chemistry	Functional group	Moon et al. (2016)
---------------------	-------------------------------	------------------	--------------------

Conclusion and Discussion

A reliable computational study of graphene-based nanomaterials should separate physical validation from quantitative refinement. The nearest-neighbor tight-binding model is extremely efficient and correctly recovers the zero-gap K-point crossing of pristine graphene, making it a useful first check of the lattice, reciprocal-space path, and orbital connectivity. DFT is then required when edge reconstruction, spin polarization, chemical bonding, charge transfer, or atom-specific defect effects become important. The PBE-PAW plane-wave framework proposed here follows established electronic-structure practice and was already widely used in graphene studies by 2017 (Kresse & Furthmüller, 1996; Kresse & Joubert, 1999; Li & Grossman, 2017). The literature indicates that no single geometric parameter controls all graphene-derived band structures. Armchair ribbon gaps are governed strongly by width and edge family, zigzag ribbons are sensitive to magnetic edge states, substitutional dopants shift carrier populations, and defects or functional groups can generate localized bands and sizable gap changes. Consequently, meaningful comparison requires consistent supercell dimensions, vacuum, k-point density, relaxation thresholds, spin settings, and band-path definitions. The proposed stepwise workflow provides that consistency and can be extended to multilayer graphene, heterostructures, adsorption systems, and transport calculations. Its main limitation is the usual DFT-PBE underestimation of semiconductor band gaps and the simplified nature of the nearest-neighbor tight-binding benchmark. For high-accuracy prediction, hybrid functionals or many-body GW corrections may be added after PBE structural relaxation, but the present protocol remains suitable for comparative trends and for a methodology-focused investigation of graphene electronic band engineering. Convergence testing is particularly important because an apparent band gap can be a numerical artifact. Sparse k-point sampling may miss the true band crossing, insufficient vacuum can couple periodic images, and an undersized defect supercell can force artificial defect-defect interactions. For zigzag ribbons, starting from a nonmagnetic state may also converge to an electronically different solution than an initialized antiferromagnetic edge configuration. Accordingly, at least three convergence checks should be reported: total energy versus plane-wave cutoff, band-edge

energies versus k-point density, and gap stability versus vacuum or supercell size. The use of Monkhorst-Pack sampling and explicitly reported tolerances makes these checks reproducible rather than dependent on software defaults (Monkhorst & Pack, 1976). Interpretation should distinguish a computational band gap from a directly measured optical or transport gap. PBE eigenvalue differences are useful for trends but can underestimate quasiparticle gaps, while experimental values may include excitonic effects, substrate screening, edge roughness, adsorbates, and finite-temperature disorder. Therefore, agreement should be assessed first at the level of qualitative physics—location of the Dirac crossing, width dependence, spin character, dopant-induced shifts, and defect-state localization—and only then through numerical gap values. This approach is consistent with the broad progression of graphene calculations from idealized band models to defect-aware and multiscale simulations (Banhart et al., 2011; Guerra et al., 2016; Li & Grossman, 2017). For reproducibility, each reported structure should be accompanied by its atomic model, lattice vectors, edge passivation, dopant or defect position, magnetic initialization, exchange-correlation functional, pseudopotential family, plane-wave cutoff, k-point grid, force threshold, and the exact reciprocal-space path used for the final bands. Saving the relaxed coordinates and self-consistent charge density is equally important because later hybrid-functional, transport, or optical calculations can then be performed without ambiguity. When these items are documented, the methodology provides a traceable basis for comparing several graphene-derived materials within one study and for separating genuine band engineering from numerical inconsistency.

References

- Banhart, F., Kotakoski, J., & Krasheninnikov, A. V. (2011). Structural defects in graphene. *ACS Nano*, 5(1), 26-41. DOI: 10.1021/nn102598m.
- Barone, V., Hod, O., & Scuseria, G. E. (2006). Electronic structure and stability of semiconducting graphene nanoribbons. *Nano Letters*, 6(12), 2748-2754. DOI: 10.1021/nl0617033.
- Castro Neto, A. H., Guinea, F., Peres, N. M. R., Novoselov, K. S., & Geim, A. K. (2009). The

electronic properties of graphene. *Reviews of Modern Physics*, 81(1), 109-162. DOI: 10.1103/RevModPhys.81.109.

Geim, A. K., & Novoselov, K. S. (2007). The rise of graphene. *Nature Materials*, 6, 183-191. DOI: 10.1038/nmat1849.

Guerra, T., Azevedo, S., & Machado, M. (2016). Defective graphene and nanoribbons: electronic, magnetic and structural properties. *European Physical Journal B*, 89, 58. DOI: 10.1140/epjb/e2016-60932-x.

Kresse, G., & Furthmüller, J. (1996). Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set. *Physical Review B*, 54, 11169-11186. DOI: 10.1103/PhysRevB.54.11169.

Kresse, G., & Joubert, D. (1999). From ultrasoft pseudopotentials to the projector augmented-wave method. *Physical Review B*, 59, 1758-1775. DOI: 10.1103/PhysRevB.59.1758.

Li, H., & Grossman, J. C. (2017). Graphene nanoribbon based thermoelectrics: controllable self-doping and long-range disorder. *Advanced Science*, 4(8), 1600467. DOI: 10.1002/advs.201600467.

Monkhorst, H. J., & Pack, J. D. (1976). Special points for Brillouin-zone integrations. *Physical Review B*, 13, 5188-5192. DOI: 10.1103/PhysRevB.13.5188.

Moon, H. S., Yun, J. M., Kim, K. H., Jang, S. S., & Lee, S. G. (2016). Investigations of the band structures

of edge-defect zigzag graphene nanoribbons using density functional theory. *RSC Advances*, 6, 39587-39594. DOI: 10.1039/C6RA03458F.

Nakada, K., Fujita, M., Dresselhaus, G., & Dresselhaus, M. S. (1996). Edge state in graphene ribbons: nanometer size effect and edge shape dependence. *Physical Review B*, 54, 17954-17961. DOI: 10.1103/PhysRevB.54.17954.

Novoselov, K. S., Geim, A. K., Morozov, S. V., Jiang, D., Zhang, Y., Dubonos, S. V., Grigorieva, I. V., & Firsov, A. A. (2004). Electric field effect in atomically thin carbon films. *Science*, 306(5696), 666-669. DOI: 10.1126/science.1102896.

Panchakarla, L. S., Subrahmanyam, K. S., Saha, S. K., Govindaraj, A., Krishnamurthy, H. R., Waghmare, U. V., & Rao, C. N. R. (2009). Synthesis, structure, and properties of boron- and nitrogen-doped graphene. *Advanced Materials*, 21(46), 4726-4730. DOI: 10.1002/adma.200901285.

Perdew, J. P., Burke, K., & Ernzerhof, M. (1996). Generalized gradient approximation made simple. *Physical Review Letters*, 77, 3865-3868. DOI: 10.1103/PhysRevLett.77.3865.

Pereira, V. M., Castro Neto, A. H., & Peres, N. M. R. (2009). Tight-binding approach to uniaxial strain in graphene. *Physical Review B*, 80, 045401. DOI: 10.1103/PhysRevB.80.045401.

Son, Y.-W., Cohen, M. L., & Louie, S. G. (2006). Energy gaps in graphene nanoribbons. *Physical Review Letters*, 97, 216803. DOI: 10.1103/PhysRevLett.97.216803.