



Investigation of Thermoelectric Properties of Nanostructured Materials for Energy Harvesting Systems

¹Wanchai Navaratnam

¹Department of Computer Science and Engineering, Daehan Institute of Management and Logistics, South Korea

¹wanchai.navaratnam@diml-kr.org

Peer Review Information

Submission: 01 Oct 2019

Revision: 15 Nov 2019

Acceptance: 30 Dec 2019

Keywords

thermoelectric materials, nanostructures, energy harvesting, Seebeck coefficient, figure of merit (ZT)

Abstract

Nanostructured thermoelectric materials offer a direct route for recovering low- and medium-grade heat because nanoscale interfaces can suppress phonon-mediated heat transport while preserving useful electronic transport. This methodology paper presents a reproducible framework for investigating the thermoelectric behavior of nanostructured Bi-Sb-Te-, PbTe-, or SnSe-based materials intended for energy-harvesting systems. The procedure combines controlled nanostructure synthesis, structural and microstructural characterization, temperature-dependent measurement of the Seebeck coefficient, electrical conductivity and thermal conductivity, and calculation of power factor and dimensionless figure of merit (ZT). The design uses a bulk or coarse-grained composition as the control and a nanostructured counterpart as the experimental group, with replicate specimens and uncertainty propagation. The methodology is grounded in literature published up to 2019, including quantum-confinement concepts, nanocomposite phonon scattering, hierarchical architectures, and device-level energy-harvesting considerations. A literature-benchmarked analysis indicates that effective nanostructuring is expected to reduce lattice thermal conductivity more strongly than it reduces electrical transport, thereby increasing ZT. An illustrative calculation at 350 K shows how decreasing thermal conductivity from 1.50 to 0.75 W m⁻¹ K⁻¹ while maintaining comparable electrical conductivity can increase ZT from about 0.60 to 1.47. These values are demonstrative, not new experimental measurements. The proposed approach provides a practical basis for comparing nanostructure-processing routes and selecting materials for compact thermoelectric generators, waste-heat recovery modules, and self-powered sensor systems.

Introduction

Thermoelectric (TE) conversion is a solid-state process in which a temperature difference is converted directly into electrical voltage through the Seebeck effect. Its attraction for energy harvesting comes from the absence of moving parts, quiet operation, scalability and the ability to use heat that would otherwise be lost. Practical applications range from industrial and

automotive waste-heat recovery to remote sensors and wearable electronics [5,11,12]. The central materials challenge is that high electrical conductivity, a large Seebeck coefficient and low thermal conductivity are not independent properties. Their combined influence is summarized by $ZT = S^2\sigma T/\kappa$, where S is Seebeck coefficient, σ is electrical conductivity, T is

absolute temperature and κ is total thermal conductivity [4,10].

Nanostructuring provides a way to partially decouple these competing transport quantities. The original low-dimensional theory predicted that quantum wells and quantum wires could modify the electronic density of states and enhance thermoelectric performance [1]. Subsequent experiments demonstrated large improvements in thin-film superlattices [2], while nanocomposites and nanocrystalline bulk materials made the approach more compatible with conventional module fabrication [3,6,7]. The key physical mechanism is selective scattering: interfaces, grain boundaries, point defects and nanoscale precipitates scatter heat-carrying phonons across different mean-free-path ranges, whereas carefully engineered electronic bands and interfaces can retain acceptable carrier mobility [7,8,13].

This study therefore focuses on a methodology rather than on a single chemistry. It is designed to determine whether a selected nanostructured material exhibits a statistically meaningful improvement in thermoelectric performance over its bulk reference, to identify which transport parameter causes that improvement, and to translate the measured material behavior into an energy-harvesting performance estimate. The paper uses only references published up to 2019, in accordance with the specified literature cutoff.

Literature Review

Hicks and Dresselhaus established the theoretical basis for low-dimensional thermoelectrics by showing that quantum-well structures can increase the thermoelectric figure of merit through changes in the electronic density of states [1]. Venkatasubramanian et al. later demonstrated high room-temperature performance in Bi₂Te₃/Sb₂Te₃ superlattice thin films, establishing that nanoscale layering can alter both electron and phonon transport [2]. Dresselhaus et al. broadened this concept to low-dimensional and bulk nanocomposite systems, emphasizing the possibility of simultaneously improving the power factor and lowering thermal conductivity [3].

The broader materials-design framework was summarized by Snyder and Toberer, who highlighted the need for electron-crystal/phonon-glass behavior and the use of complex chemistry and structure to lower lattice thermal conductivity without destroying electronic transport [4]. Bell linked such material improvements to real thermoelectric systems and showed that device architecture, heat exchangers and usable temperature difference are as important as material ZT for practical waste-heat recovery [5].

A major bulk-nanostructuring milestone was reported by Poudel et al., who used ball milling and hot pressing to create nanocrystalline p-type Bi-Sb-Te with a peak ZT of approximately 1.4 near 100 °C; the improvement was primarily associated with enhanced phonon scattering at grain boundaries and defects [6]. Minnich et al. subsequently reviewed bulk nanostructured thermoelectrics and identified the need to understand carrier and phonon transport across multiple length scales [7]. Hierarchical structuring was advanced by Biswas et al., who combined atomic-scale disorder, nanoscale precipitates and mesoscale grain boundaries in PbTe-based materials to scatter a broad phonon spectrum [8].

Materials with intrinsically weak heat transport provide another route. Zhao et al. reported ultralow thermal conductivity and high ZT in anisotropic SnSe, demonstrating the strong role of anharmonic bonding and crystal structure [9]. He and Tritt later reviewed the field and identified band engineering, defect chemistry, nanostructuring and improved transport understanding as major routes to further progress [10]. For energy harvesting, Petsagkourakis et al. emphasized near-room-temperature inorganic, hybrid and organic materials for sensors and wearable systems [11], while Selvan et al. reviewed bulk, thick-film and thin-film generator methodologies and device-level performance metrics [12]. By 2019, computational studies explicitly coupled phase stability, band alignment, band convergence and vibrational anharmonicity to guide nanostructure design [13], and two- and three-dimensional nanostructuring strategies were being used to suppress κ and exploit energy filtering [14].

Table 1. Selected literature milestones supporting the methodology (cutoff: 2019)

Study	Material / concept	Methodological relevance	Key outcome
-------	--------------------	--------------------------	-------------

[1] Hicks & Dresselhaus, 1993	Quantum wells	Motivates low-dimensional control of electronic states	Predicted enhanced TE figure of merit
[2] Venkatasubramanian et al., 2001	Bi ₂ Te ₃ /Sb ₂ Te ₃ superlattice	Thin-film benchmark and interface engineering	High room-temperature ZT reported
[6] Poudel et al., 2008	Nanocrystalline Bi-Sb-Te	Ball milling + hot pressing; grain-boundary scattering	Peak ZT $\approx$ 1.4 near 373 K
[8] Biswas et al., 2012	Hierarchical PbTe-based bulk	Multi-length-scale defect architecture	Strong κ reduction with high ZT
[9] Zhao et al., 2014	SnSe single crystals	Intrinsic low κ / anisotropic transport benchmark	Very high high-temperature ZT
[13] Hao et al., 2019	Nanostructured bulk TE design	Links phase stability, band alignment and phonon scattering	Theory-guided optimization framework

Methodology

1. Research Design and Material Selection

A controlled comparative design will be used. For each selected chemistry, two specimen classes will be prepared: (A) a bulk/coarse-grained reference and (B) a nanostructured specimen with nominally the same composition. A near-room-temperature Bi-Sb-Te system is recommended for energy-harvesting demonstrations because it is well established in low-grade heat conversion [6,11]. PbTe-based or SnSe-based materials may be used when the intended operating range is higher [8,9]. At least three independently prepared pellets or films per condition should be tested so that processing variability is not confused with instrumental repeatability.

2. Nanostructure Preparation

For a bulk nanocrystalline route, precursor ingots or powders are weighed to the target stoichiometry under controlled atmosphere. The material is mechanically alloyed or ball-milled to reduce particle and crystallite size, followed by densification by hot pressing or spark-plasma sintering (SPS). Processing temperature, pressure, dwell time, milling duration and atmosphere are recorded as independent variables. The bulk reference is consolidated with reduced milling intensity or from coarse precursor powder. This design follows the logic of nanocrystalline Bi-Sb-Te processing [6] and hierarchical bulk nanostructuring [7,8]. If thin films are investigated, deposition thickness, substrate temperature and annealing conditions replace the consolidation variables [2,12].

3. Structural and Microstructural Characterization

- X-ray diffraction (XRD): identify phase purity, secondary phases and approximate crystallite size; compare peak broadening between bulk and nanostructured specimens.
- Scanning electron microscopy (SEM): determine grain morphology, porosity and fracture-surface uniformity; analyze at least five fields of view per specimen.
- Transmission electron microscopy (TEM), where available: measure nanoscale grains/precipitates and examine interfaces responsible for phonon scattering.
- Density measurement: determine relative density by geometric or Archimedes method because residual porosity can lower both electrical and thermal transport.

4. Thermoelectric Transport Measurements

The Seebeck coefficient $S(T)$ and electrical conductivity $\sigma(T)$ are measured over the intended operating range, for example 300–500 K for Bi-Sb-Te energy-harvesting materials. A four-probe method is preferred for electrical resistivity to minimize contact resistance; conductivity is obtained as $\sigma = 1/\rho$. Seebeck voltage is recorded under a controlled small temperature difference and calculated from the slope $\Delta V/\Delta T$. Measurements should be repeated during heating and cooling to identify irreversible microstructural or contact effects.

Thermal conductivity is determined from $\kappa = D \cdot C_p \cdot \rho_m$, where D is thermal diffusivity, C_p is specific heat capacity and ρ_m is mass density. Laser-flash analysis is suitable for dense pellets; steady-state or 3ω -type approaches may be used for films. Where Hall measurements are available, carrier concentration and mobility are also determined to establish whether changes in

σ originate from carrier density or interface/grain-boundary scattering. Electronic thermal conductivity may be estimated using the

Wiedemann–Franz relation $\kappa_e = L\sigma T$, allowing lattice thermal conductivity $\kappa_L = \kappa - \kappa_e$ to be discussed cautiously [4,7,13].




Figure 1. Proposed workflow for linking nanostructure processing, transport measurements and energy-harvesting performance.

5. Calculation of Performance Metrics

At each measurement temperature, power factor is calculated as $PF = S^2\sigma$ and dimensionless figure of merit as $ZT = S^2\sigma T/\kappa$. The primary response variable is the percentage change in ZT between the nanostructured and bulk groups at matched temperature. Secondary responses are κ_L reduction, PF retention or enhancement, and the temperature at which maximum ZT occurs. For device relevance, the open-circuit voltage of a thermoelectric leg or module may be approximated by integrating $S(T)dT$ across the measured temperature range; a first-order estimate is $V_{oc} \approx S_{avg}\Delta T$ for a limited ΔT .

6. Statistical and Uncertainty Analysis

Each reported property should be expressed as mean $\pm$ standard deviation for independently prepared specimens. The nanostructured and bulk groups are compared using an independent-samples t-test at matched temperatures when normality and variance assumptions are acceptable; otherwise, a Mann–Whitney test is used. For temperature-series data, a two-factor analysis (processing condition $\times$ temperature) or mixed-effects model is preferable. Measurement uncertainty from S , σ and κ is propagated to ZT using the root-sum-square approximation. A result is considered practically meaningful only when the ZT improvement is larger than the combined experimental uncertainty and is accompanied by a physically consistent microstructural explanation.

7. Energy-Harvesting System Evaluation

The final stage translates material data to a simple generator assessment. A representative hot-side and cold-side temperature are selected from the target application, such as an industrial surface and ambient air or a human-body/ambient gradient for low-power sensing. The predicted open-circuit voltage, internal

resistance and matched-load power are estimated from measured transport properties and the geometry of the thermoelectric legs. This prevents selection of a material solely on peak ZT : a useful energy harvester must also provide adequate power density, thermal coupling, mechanical reliability and a stable temperature gradient [5,11,12].

8. Quality Control and Reproducibility

Instrument calibration is checked with certified or well-characterized reference materials before each measurement series. Sample dimensions, contact geometry and surface preparation are documented because errors in thickness or probe spacing directly affect calculated transport coefficients. At least one specimen is remeasured after remounting to assess contact sensitivity. Microstructural measurements are performed on multiple regions rather than a single representative image, and raw voltage, temperature and diffusivity data are retained so that derived quantities can be independently recalculated. These controls are particularly important in nanostructured thermoelectrics because local porosity, preferred orientation and interfacial phases may create substantial specimen-to-specimen variability.

Results

Because the present work defines a methodology and does not report newly performed laboratory experiments, the numerical values in Table 2 are an illustrative calculation used to demonstrate how the proposed analysis would be interpreted. They are not claimed as new experimental data. The trend is deliberately consistent with the physical behavior reported for nanostructured thermoelectrics: thermal conductivity is reduced strongly by phonon scattering, while the power factor is retained or moderately changed [3,6–8,13,14].

Table 2. Illustrative transport-property calculation at 350 K (method demonstration only)

Condition	S ($\mu\text{V/K}$)	σ (S/m)	κ ($\text{W/m}\cdot\text{K}$)	PF ($\text{mW/m}\cdot\text{K}^2$)	Calculated ZT
Bulk reference	180	8.0×10^4	1.50	2.59	0.60
Nanostructured	205	7.5×10^4	0.75	3.15	1.47

In the illustrative comparison, the Seebeck coefficient increases from 180 to 205 $\mu\text{V K}^{-1}$ and electrical conductivity decreases slightly from 8.0×10^4 to 7.5×10^4 S m^{-1} . The resulting power factor therefore rises from 2.59 to 3.15 $\text{mW m}^{-1} \text{K}^{-2}$. The dominant change is the 50% reduction in total thermal conductivity from 1.50 to 0.75 $\text{W m}^{-1} \text{K}^{-1}$. Substitution into $ZT = S^2\sigma T/\kappa$ gives approximately 0.60 for the bulk reference and 1.47 for the nanostructured material at 350 K. Such a result would support the hypothesis that nanoscale interfaces suppress phonon heat transport more strongly than they suppress useful electrical transport.

The microstructural evidence required to support this interpretation would include a reduced grain size, a high density of clean grain boundaries or nanoscale precipitates, and no large secondary-phase fraction that could electrically isolate the matrix. If κ decreases but σ collapses, the nanostructure would be judged over-scattered or insufficiently dense. Conversely, if PF increases while κ is unchanged, the improvement would point to electronic structure or energy-filtering effects rather than mainly phonon scattering. The methodology therefore treats ZT as an endpoint but not as the only diagnostic variable.

For an energy-harvesting interpretation, the same data would be replotted against the temperature range expected in the intended application rather than only at the peak-ZT temperature. A material that maintains a moderate ZT over a broad range can be more useful than one with a narrow maximum. Under a fixed module geometry, the nanostructured condition would be expected to provide a larger voltage-normalized power output when the gain in Seebeck coefficient and reduction in parasitic heat conduction compensate for any increase in electrical resistance. This application-window analysis connects the laboratory material measurements to the practical criteria emphasized in generator studies [5,11,12].

Conclusion and Discussion

The proposed methodology provides an experimentally defensible route for investigating

nanostructured thermoelectric materials for energy harvesting. Its main strength is the use of matched bulk and nanostructured specimens, which permits the effect of nanoscale features to be separated from composition. The combination of XRD, SEM/TEM, electrical transport and thermal transport establishes a chain of evidence from processing to structure to performance. This is essential because an apparent increase in ZT can otherwise be misinterpreted if density, contact resistance or phase composition is not controlled. The literature up to 2019 shows three complementary design principles. First, low-dimensional or nanostructured features can alter electronic states and scatter phonons [1–3]. Second, bulk nanocrystalline and hierarchical architectures can scatter heat-carrying phonons over several length scales while retaining device-compatible geometry [6–8]. Third, band engineering and intrinsically low thermal conductivity can be combined with nanostructuring to raise performance further [9,10,13,14]. For energy-harvesting systems, however, peak material ZT must be considered together with the available temperature difference, electrical resistance, heat-transfer losses, mechanical stability and fabrication cost [5,11,12]. Accordingly, a successful experimental outcome would not simply be “smaller grains.” It would be a reproducible microstructure that produces a significant κL reduction, retains or enhances PF, and increases ZT across the actual application temperature window. Future work can extend the methodology to flexible thin films, nanowires, segmented modules and computationally optimized precipitate systems. Within the 2019 literature boundary, the evidence strongly supports nanostructure engineering as one of the most effective approaches for improving thermoelectric energy conversion while preserving the solid-state reliability needed for autonomous energy-harvesting devices. Mechanistically, the most convincing evidence of a nanostructure benefit would be a reduction in lattice thermal conductivity that correlates with the measured grain or precipitate size, while Hall mobility remains sufficiently high to prevent a severe loss in electrical conductivity. This balance is consistent with the multiscale-scattering picture

developed for bulk nanostructured and hierarchical thermoelectrics [7,8,13]. If a Seebeck enhancement is also observed, its origin should be tested against carrier-concentration changes and possible interface energy filtering rather than assigned automatically to quantum confinement. In comparatively thick or bulk specimens, classical boundary scattering is often more plausible than strong electronic confinement unless a genuinely low-dimensional feature size is demonstrated [1,3,14]. Several limitations should be recognized before translating a laboratory ZT improvement into an energy-harvesting claim. Nanostructures may coarsen during prolonged operation, oxidation or volatilization can change carrier concentration, and anisotropic materials such as SnSe require careful control of measurement direction [9]. Dense contacts and low electrical/thermal interface resistances are essential at module level; otherwise, material improvements are partly lost in packaging [5,12]. Composition also affects cost, abundance and environmental acceptability, especially for Pb- or Te-containing systems. For these reasons, the final material ranking should include stability after thermal cycling, density, repeatability, ease of scale-up and attainable power under the intended temperature gradient in addition to peak ZT. This broader evaluation makes the methodology suitable for selecting candidates that can realistically progress from nanostructure research to energy-harvesting devices.

References

- Hicks, L. D., & Dresselhaus, M. S. (1993). Effect of quantum-well structures on the thermoelectric figure of merit. *Physical Review B*, 47(19), 12727–12731. DOI: 10.1103/PhysRevB.47.12727.
- Venkatasubramanian, R., Siivola, E., Colpitts, T., & O'Quinn, B. (2001). Thin-film thermoelectric devices with high room-temperature figures of merit. *Nature*, 413, 597–602. DOI: 10.1038/35098012.
- Dresselhaus, M. S., Chen, G., Tang, M. Y., Yang, R. G., Lee, H., Wang, D. Z., Ren, Z. F., Fleurial, J.-P., & Gogna, P. (2007). New directions for low-dimensional thermoelectric materials. *Advanced Materials*, 19(8), 1043–1053. DOI: 10.1002/adma.200600527.
- Snyder, G. J., & Toberer, E. S. (2008). Complex thermoelectric materials. *Nature Materials*, 7, 105–114. DOI: 10.1038/nmat2090.
- Bell, L. E. (2008). Cooling, heating, generating power, and recovering waste heat with thermoelectric systems. *Science*, 321(5895), 1457–1461. DOI: 10.1126/science.1158899.
- Poudel, B., Hao, Q., Ma, Y., Lan, Y., Minnich, A., Yu, B., Yan, X., Wang, D., Muto, A., Vashaee, D., Chen, X., Liu, J., Dresselhaus, M. S., Chen, G., & Ren, Z. (2008). High-thermoelectric performance of nanostructured bismuth antimony telluride bulk alloys. *Science*, 320(5876), 634–638. DOI: 10.1126/science.1156446.
- Minnich, A. J., Dresselhaus, M. S., Ren, Z. F., & Chen, G. (2009). Bulk nanostructured thermoelectric materials: current research and future prospects. *Energy & Environmental Science*, 2, 466–479. DOI: 10.1039/B822664B.
- Biswas, K., He, J., Blum, I. D., Wu, C.-I., Hogan, T. P., Seidman, D. N., Dravid, V. P., & Kanatzidis, M. G. (2012). High-performance bulk thermoelectrics with all-scale hierarchical architectures. *Nature*, 489, 414–418. DOI: 10.1038/nature11439.
- Zhao, L.-D., Lo, S.-H., Zhang, Y., Sun, H., Tan, G., Uher, C., Wolverton, C., Dravid, V. P., & Kanatzidis, M. G. (2014). Ultralow thermal conductivity and high thermoelectric figure of merit in SnSe crystals. *Nature*, 508, 373–377. DOI: 10.1038/nature13184.
- He, J., & Tritt, T. M. (2017). Advances in thermoelectric materials research: Looking back and moving forward. *Science*, 357(6358), eaak9997. DOI: 10.1126/science.aak9997.
- Petsagkourakis, I., Tybrandt, K., Crispin, X., Ohkubo, I., Satoh, N., & Mori, T. (2018). Thermoelectric materials and applications for energy harvesting power generation. *Science and Technology of Advanced Materials*, 19(1), 836–862. DOI: 10.1080/14686996.2018.1530938.
- Selvan, K. V., Hasan, M. N., & Mohamed Ali, M. S. (2019). Methodological reviews and analyses on the emerging research trends and progress of thermoelectric generators. *International Journal of Energy Research*, 43, 113–140. DOI: 10.1002/er.4206.
- Hao, S., Dravid, V. P., Kanatzidis, M. G., & Wolverton, C. (2019). Computational strategies for design and discovery of nanostructured thermoelectrics. *npj Computational Materials*, 5, 58. DOI: 10.1038/s41524-019-0197-9.
- Novak, T. G., Kim, K., & Jeon, S. (2019). 2D and 3D nanostructuring strategies for thermoelectric

materials. *Nanoscale*, 11, 19684–19699. DOI:
10.1039/C9NR07406F.