



Study of Magnetic Phase Transitions in Rare-Earth Compounds

¹Korinna Belhocine

¹Department of Electrical and Computer Engineering, Siam Delta Engineering Institute, Thailand

¹korinna.belhocine@sdei-th.edu

Peer Review Information

Submission: 18 Sep 2021

Revision: 02 Oct 2021

Acceptance: 27 Nov 2021

Keywords

rare-earth compounds, magnetic phase transition, Arrott plot, magnetocaloric effect, magneto structural coupling

Abstract

Rare-earth compounds exhibit a wide spectrum of magnetic phase transitions because localized 4f moments interact with crystal fields, conduction electrons, lattice strain, and, in many intermetallics, transition-metal 3d states. This methodology paper presents a reproducible framework for identifying the transition temperature and classifying a transition as first-order, second-order, antiferromagnetic, ferromagnetic, or metamagnetic. The workflow combines phase verification by X-ray diffraction, temperature-dependent magnetization, Curie-Weiss analysis, field-dependent magnetization, Arrott/Banerjee criteria, and magnetic-entropy scaling. Literature-reported rare-earth systems up to 2021 are used as benchmarks rather than as new experimental measurements. The benchmark comparison shows that Gd₅Si₂Ge₂-based alloys can move between first- and second-order behavior through thermal processing or chemical substitution, while Al₁₃C₃ compounds display rare-earth-dependent ferromagnetic and antiferromagnetic states. The proposed method therefore links structural state, magnetic response, and thermodynamic signatures in a single analysis sequence. It is suitable for rare-earth intermetallics and related compounds where coupled magnetic and lattice degrees of freedom control functional properties such as magnetocaloric response, magnetostriction, and reversible field-induced phase switching.

Introduction

Magnetic phase transitions are central to condensed-matter physics because they provide a direct route for studying how microscopic exchange interactions produce collective order. Rare-earth compounds are particularly informative systems. Their partially filled 4f shells generate large localized moments, strong spin-orbit coupling, and substantial magnetocrystalline anisotropy. The magnetic ground state is then determined by competition among indirect exchange, crystal-electric-field effects, lattice symmetry, and, in rare-earth-transition-metal compounds, coupling between 4f and 3d electronic subsystems. Consequently, closely related compositions can show ferromagnetic (FM), antiferromagnetic (AFM),

ferrimagnetic, metamagnetic, or multi-step transitions over a broad temperature range.

The practical importance of these transitions increased greatly after the observation of a giant magnetocaloric effect in Gd₅Si₂Ge₂, where a large entropy change is associated with a coupled magnetic and structural transformation [3]. This result established rare-earth intermetallics as model materials in which the order of a transition is not only a fundamental classification but also a design parameter for magnetic refrigeration, thermal-expansion control, and field-responsive functionality. Pressure experiments on Gd₅Si₂Ge₂ later demonstrated that the transition temperature and magnetoelastic coupling are strongly tunable, emphasizing that

the lattice cannot be treated as a passive background [4].

A major methodological difficulty is that a sharp magnetization change alone does not prove a first-order transition. Classical magnetic-isotherm analysis provides more reliable tests. Arrott introduced an equation-of-state method in which magnetic isotherms are transformed to reveal the onset of ferromagnetism [1], and Banerjee subsequently showed that the sign of the slope in an Arrott representation can be used as a criterion for first- versus second-order behavior [2]. Modern magnetocaloric scaling adds complementary diagnostics: second-order transitions tend to collapse onto a universal entropy-change curve [5,6], while a field exponent n greater than 2 near the transition provides a quantitative fingerprint of first-order thermomagnetic behavior [10].

The objective of this paper is therefore to define a step-by-step methodology for studying magnetic phase transitions in rare-earth compounds and to demonstrate how the method is interpreted using published benchmark systems reported no later than 2021. The emphasis is on reproducibility: structural verification is performed before magnetic classification, transition temperatures are extracted by explicit criteria, and at least two independent tests are used to assign transition order.

Literature Review

The literature shows that magnetic transition order in rare-earth compounds is highly sensitive to structure and composition. Pecharsky and Gschneidner reported the giant magnetocaloric effect of $\text{Gd}_5\text{Si}_2\text{Ge}_2$ near room temperature and linked the unusually large response to a sharp magnetic transformation [3]. Subsequent work established that this system is magnetostructural: hydrostatic pressure shifts the Curie temperature strongly and modifies the critical field, indicating pronounced magnetoelastic coupling [4]. This behavior is important methodologically because magnetization measurements should be interpreted together with crystallographic information whenever a rare-earth compound lies near a structural phase boundary.

Thermal history is another major control variable. Belo et al. showed that annealing $\text{Gd}_5\text{Si}_2\text{Ge}_2$ alters the monoclinic and

orthorhombic phase fractions and can change the observed transition from second-order-like to first-order; their study also used Arrott analysis to track the change in transition character [7]. Chemical substitution produces a comparable effect. In $\text{Gd}_{5-x}\text{Nd}_x\text{Si}_2\text{Ge}_2$, Uthaman et al. found a first-order transition at 275 K for $x = 0.05$, whereas $x = 0.10$ and 0.20 stabilized an orthorhombic phase and showed second-order transitions around 300 and 293 K, respectively [8]. These observations show why phase fraction, lattice symmetry, and composition must be included in a magnetic-transition methodology rather than treated as separate materials-characterization tasks.

Disorder and competing exchange can also generate multiple magnetic regimes. Cobalt-substituted $\text{Gd}_5\text{Si}_2\text{Ge}_2$ displayed both first- and second-order transitions together with short-range ferromagnetic correlations; entropy-change scaling was used to assess transition order [9]. A broader thermodynamic perspective was provided by Bonilla et al., who compared RCo_2 Laves phases and manganites and showed that normalized magnetic-entropy curves collapse for second-order transitions but not for first-order cases [5]. Franco and Conde formalized the scaling procedure and its use for magnetocaloric characterization [6]. Law et al. later proposed a model-independent quantitative criterion based on the field exponent of the entropy change, reducing the subjectivity of purely visual phase-transition classification [10].

Rare-earth-transition-metal Laves phases illustrate the strong coupling of magnetic order and lattice response. Hu et al. tuned cubic $(\text{Gd,R})(\text{Co,Fe})_2$ compounds ($R = \text{Dy, Ho, Er}$) from abrupt first-order behavior toward second-order behavior and associated this control with rare-earth-moment-driven volume magnetostriction [11]. More recent work up to 2021 explored transition control near structural boundaries in other rare-earth intermetallics. Yu et al. reported a crossover from second-order behavior toward first-order-like, hysteresis-free metamagnetism in $\text{Gd}_2\text{In}_{1-x}\text{Al}_x$ near a hexagonal-to-orthorhombic boundary [12]. Liu et al. similarly obtained a nonhysteretic metamagnetic transition in $\text{Ho}_2\text{In}_{1-x}\text{Al}_x$ through heterostructural alloying [13].

Table 1. Selected literature benchmarks for magnetic phase-transition studies.

System / study	Main transition evidence	Methodological significance
----------------	--------------------------	-----------------------------

Gd ₅ Si ₂ Ge ₂ [3,4]	Coupled magnetic-structural transition; pressure-sensitive TC	Structure and magnetism must be analyzed together
Annealed Gd ₅ Si ₂ Ge ₂ [7]	Thermal treatment changes phase fraction and transition order	Control and report heat-treatment history
Gd ₅ -xNd _x Si ₂ Ge ₂ [8]	x=0.05: FOPT at 275 K; x=0.10, 0.20: SOPT near 300, 293 K	Composition can switch FOPT/SOPT
Gd ₅ Si ₂ -xCoxGe ₂ [9]	Double transitions and short-range FM correlations	Use dense temperature scans and entropy scaling
RCo ₂ -based alloys [11]	Tunable first-to-second-order character with magnetostriction	Include lattice-coupling evidence
RA ₁₃ C ₃ [14]	FM, AFM, and two-step behavior across rare-earth ions	Same structure can host different magnetic ground states

Methodology

The proposed protocol is designed for a polycrystalline rare-earth compound or composition series and can be applied directly to intermetallic families such as RA₁₃C₃, RCo₂-based alloys, Gd-Si-Ge derivatives, or R₂In-based materials. The procedure is divided into seven sequential steps.

Step 1 - Sample definition and synthesis. Select either a rare-earth series (vary R while retaining the same structure) or a controlled substitution series. For intermetallic samples, weigh high-purity constituent elements according to nominal stoichiometry and synthesize under inert argon by arc melting or another validated solid-state route. Remelt multiple times for chemical homogeneity. If the phase diagram indicates heat-treatment sensitivity, anneal specimens under vacuum or inert atmosphere and document temperature, duration, and cooling rate. Thermal history must be treated as an experimental variable because it can change phase fractions and transition order, as shown for Gd₅Si₂Ge₂ [7].

Step 2 - Structural verification. Collect powder X-ray diffraction (XRD) data at room temperature using Cu K-alpha radiation or an equivalent calibrated source. Perform Rietveld refinement to determine space group, lattice parameters, phase fraction, and fit quality. A sample is accepted for magnetic classification only when the dominant phase is identified and impurity phases are quantified. If a first-order magnetostructural transition is suspected, repeat XRD below and above the transition temperature or use temperature-dependent diffraction. This requirement is supported by pressure and substitution studies in which structural changes accompany magnetic changes [4,8].

Step 3 - Temperature-dependent magnetization. Measure zero-field-cooled (ZFC) and field-cooled (FC) magnetization $M(T)$ in a small probing field,

typically 0.01-0.10 T, over a temperature interval that extends well below and above the expected transition. Use a temperature step of 2-5 K far from the anomaly and 0.5-1 K within approximately ± 15 K of it. Estimate the transition temperature from the maximum in $|dM/dT|$ for a ferromagnetic transition, from the cusp or derivative anomaly for an antiferromagnetic transition, and from any separation between heating and cooling traces for hysteresis. A second anomaly is recorded as a separate transition rather than absorbed into a broadened single transition; this is important for systems such as DyAl₁₃C₃ and Co-substituted Gd-Si-Ge [9,14].

Step 4 - Paramagnetic Curie-Weiss analysis. Above the highest transition temperature, calculate susceptibility $\chi = M/H$ and fit the inverse susceptibility to $\chi = C/(T - \theta_p)$. The Curie constant C gives an effective magnetic moment, while the sign and magnitude of θ_p provide an initial indication of dominant exchange. Agreement between the experimental effective moment and the free-ion rare-earth value supports the localized 4f-moment picture; large deviations may indicate crystal-field effects, mixed valence, itinerant contributions, or secondary phases. The Curie-Weiss fit must exclude the critical region immediately above the transition to minimize short-range-correlation bias.

Step 5 - Isothermal magnetization and Arrott/Banerjee test. Measure $M(H)$ isotherms over a symmetric or positive field range (for example 0-5 or 0-7 T) at closely spaced temperatures around the transition. Construct conventional Arrott plots of M^2 versus H/M [1]. According to the Banerjee criterion, a negative-slope region indicates first-order character, whereas consistently positive slopes support a second-order transition [2]. Where ordinary Arrott plots are strongly curved, use modified Arrott plots or critical-exponent analysis, but

retain the slope test as one part of a multi-criterion decision.

Step 6 - Magnetic entropy and transition-order cross-check. From the $M(H,T)$ data, calculate the isothermal magnetic-entropy change using the discrete Maxwell relation: $\Delta S_M(T, \Delta H)$ is approximated by the field integral of $(\partial M / \partial T)_H dH$. Normalize ΔS_M curves obtained under different fields and test whether they collapse onto a universal curve. Collapse supports second-order behavior [5,6], whereas systematic non-collapse supports first-order behavior. In addition, calculate the local field exponent $n = d \ln |\Delta S_M| / d \ln H$. A maximum $n > 2$ near the transition is a quantitative fingerprint of a first-order thermomagnetic transition [10].

Step 7 - Final classification and reproducibility. Assign the magnetic state from the combined $M(T)$, $M(H)$, hysteresis, Curie-Weiss, and structural evidence. Assign transition order only when at least two independent criteria agree. For example, a first-order assignment should ideally include thermal/magnetic hysteresis or structural discontinuity together with a negative-slope Arrott region, entropy-curve non-collapse, or $n > 2$. A second-order assignment should show negligible hysteresis, positive Arrott slopes, and entropy-curve collapse. Repeat measurements on at least two independently prepared specimens or on repeated thermal cycles to test reproducibility. Report uncertainty in transition temperature from the temperature step and derivative-peak width.




Figure 1. Step-by-step workflow for structural verification, magnetic measurement, and phase-transition classification.

Results

Because no original magnetization or diffraction dataset was supplied, this section reports a benchmark application of the proposed workflow to published rare-earth systems; the values are literature results, not newly measured data. The comparison confirms that the methodology produces physically consistent classifications across different families.

For $\text{Gd}_5\text{Si}_2\text{Ge}_2$ -derived materials, the strongest result is the close relation between structure and transition order. The parent system is a canonical magnetostructural material [3,4]. Annealing can increase the monoclinic phase fraction and convert second-order-like behavior into a first-order transition [7]. Nd substitution provides a controlled example: $\text{Gd}_{4.95}\text{Nd}_{0.05}\text{Si}_2\text{Ge}_2$ shows a first-order transition at about 275 K, while the $x = 0.10$ and 0.20 compositions show second-order transitions at about 300 and 293 K [8]. These changes would be captured by Steps 2, 3, 5, and 6 of the present protocol through diffraction, derivative-based transition temperatures, Arrott slope, and entropy scaling.

Co substitution demonstrates why a single transition criterion is insufficient. $\text{Gd}_5\text{Si}_2\text{-xCo}_x\text{Ge}_2$ can contain both first- and second-order transitions and short-range ferromagnetic

correlations. Reported first-order magnetostructural entropy-change maxima for $x = 0.10, 0.20$, and 0.40 were approximately 9.0, 8.5, and $4.2 \text{ J kg}^{-1} \text{ K}^{-1}$ at 260, 245, and 210 K for a 5 T field change [9]. A sparse $M(T)$ scan could merge these features, whereas closely spaced isotherms and universal-curve analysis expose the coexistence of different transition regimes.

The 2021 Al_3C_3 results provide a complementary test in which the same crystallographic family supports different magnetic ground states. NdAl_3C_3 develops two AFM states; GdAl_3C_3 , TbAl_3C_3 , HoAl_3C_3 , and ErAl_3C_3 are ferromagnetic; DyAl_3C_3 shows complex transitions near 22 and 49 K; and the reported transitions are second-order without hysteresis [14]. Thus, structural similarity alone is not a sufficient classifier. The rare-earth ion controls the magnetic interaction network and must be analyzed through $M(T)$, Curie-Weiss behavior, and field response.

Finally, the RCo_2 - and R_2In -based studies show that transition order can be tuned continuously near a structural or magnetic boundary. Composition adjustment in $(\text{Gd,R})(\text{Co,Fe})_2$ converts abrupt first-order behavior toward second-order behavior while changing

magnetostriction [11]. Gd₂In_{1-x}Al_x and Ho₂In_{1-x}Al_x demonstrate first-order-like or metamagnetic behavior with very small hysteresis near competing structures [12,13].

For such borderline systems, the final decision should rely on the quantitative entropy exponent and Arrott analysis rather than hysteresis alone.

Table 2. Benchmark outcomes expected from the proposed analysis sequence.

Benchmark	Reported observation	Classification / diagnostic
Gd ₄ .95Nd _{0.05} Si ₂ Ge ₂ [8]	TC $\approx$ 275 K; monoclinic-associated sharp transition	First-order; confirm with Arrott/entropy criteria
Gd ₄ .90Nd _{0.10} Si ₂ Ge ₂ [8]	TC $\approx$ 300 K; orthorhombic phase	Second-order
Gd ₄ .80Nd _{0.20} Si ₂ Ge ₂ [8]	TC $\approx$ 293 K; orthorhombic phase	Second-order
Gd ₅ Si _{1.9} Co _{0.1} Ge ₂ [9]	$-\Delta S M \approx 9.0 \text{ J kg}^{-1} \text{ K}^{-1}$ at 260 K (5 T)	First-order magnetostructural component
DyAl ₃ C ₃ [14]	Two anomalies near 22 K and 49 K; nonhysteretic	Complex, second-order transitions
Ho ₂ In _{1-x} Al _x near x=0.1 [13]	Metamagnetic response with minimal hysteresis	Borderline transition: use quantitative cross-checks

Conclusion and Discussion

This paper presents a compact methodology for studying magnetic phase transitions in rare-earth compounds using a linked structural, magnetic, and thermodynamic workflow. The key methodological principle is that transition classification should never depend on a single sharp feature in $M(T)$. XRD establishes the structural state; ZFC/FC magnetization locates the transition; Curie-Weiss fitting characterizes the paramagnetic regime; $M(H)$ isotherms and Arrott/Banerjee plots test transition order; and magnetic-entropy scaling supplies an independent thermodynamic cross-check. The literature benchmarks show why this combined approach is necessary. Gd₅Si₂Ge₂-based systems can switch between first- and second-order behavior through annealing or substitution, RAl₃C₃ compounds can host very different FM and AFM states within the same structural family, and RCo₂- or R₂In-based materials can lie near a first-order/second-order boundary with little hysteresis. Therefore, future experimental studies should report structural phase fraction, heating/cooling protocol, field history, temperature step, and at least two transition-order criteria. With those controls, the methodology provides a reproducible basis for comparing rare-earth compounds and for linking magnetic phase transitions to magnetocaloric, magnetostrictive, and other functional responses.

References

Arrott, "Criterion for Ferromagnetism from Observations of Magnetic Isotherms," *Physical Review*, 108(6), 1394-1396 (1957). DOI: 10.1103/PhysRev.108.1394

K. Banerjee, "On a Generalised Approach to First and Second Order Magnetic Transitions," *Physics Letters*, 12(1), 16-17 (1964). DOI: 10.1016/0031-9163(64)91158-8

V. K. Pecharsky and K. A. Gschneidner Jr., "Giant Magnetocaloric Effect in Gd₅(Si₂Ge₂)," *Physical Review Letters*, 78(23), 4494-4497 (1997). DOI: 10.1103/PhysRevLett.78.4494

Magen, L. Morellon, P. A. Algarabel, M. R. Ibarra, Z. Arnold, J. Kamarad, T. A. Lograsso, D. L. Schlager, V. K. Pecharsky, A. O. Tsokol, and K. A. Gschneidner Jr., "Hydrostatic Pressure Control of the Magnetostructural Phase Transition in Gd₅Si₂Ge₂ Single Crystals," *Physical Review B*, 72, 024416 (2005). DOI: 10.1103/PhysRevB.72.024416

[5] C. M. Bonilla, J. Herrero-Albillos, F. Bartolome, L. M. Garcia, M. Parra-Borderias, and V. Franco, "Universal Behavior for Magnetic Entropy Change in Magnetocaloric Materials: An Analysis on the Nature of Phase Transitions," *Physical Review B*, 81, 224424 (2010). DOI: 10.1103/PhysRevB.81.224424

V. Franco and A. Conde, "Scaling Laws for the Magnetocaloric Effect in Second Order Phase Transitions: From Physics to Applications for the Characterization of Materials," *International Journal of Refrigeration*, 33(3), 465-473 (2010). DOI: 10.1016/j.ijrefrig.2009.12.019

J. H. Belo et al., "Phase Control Studies in Gd₅Si₂Ge₂ Giant Magnetocaloric Compound," *Journal of Alloys and Compounds*, 529, 89-95 (2012). DOI: 10.1016/j.jallcom.2012.02.164

B. Uthaman, G. R. Raji, S. Thomas, K. G. Suresh, and M. R. Varma, "Tuning the Structural and Magnetocaloric Properties of $\text{Gd}_5\text{Si}_2\text{Ge}_2$ with Nd Substitution," *Journal of Applied Physics*, 117, 013910 (2015). DOI: 10.1063/1.4905544

B. Uthaman, P. Manju, S. Thomas, D. Jaiswal Nagar, K. G. Suresh, and M. R. Varma, "Observation of Short-Range Ferromagnetic Interactions and Magnetocaloric Effect in Cobalt Substituted $\text{Gd}_5\text{Si}_2\text{Ge}_2$," *Physical Chemistry Chemical Physics*, 19, 12282-12295 (2017). DOI: 10.1039/C7CP00849J

J. Y. Law, V. Franco, L. M. Moreno-Ramirez, A. Conde, D. Y. Karpenkov, I. Radulov, K. P. Skokov, and O. Gutfleisch, "A Quantitative Criterion for Determining the Order of Magnetic Phase Transitions Using the Magnetocaloric Effect," *Nature Communications*, 9, 2680 (2018). DOI: 10.1038/s41467-018-05111-w

J. Hu, K. Lin, Y. Cao, C. Yu, W. Li, R. Huang, H. E. Fischer, K. Kato, Y. Song, J. Chen, H. Zhang, and X. Xing, "Adjustable Magnetic Phase Transition Inducing Unusual Zero Thermal Expansion in

Cubic RCo_2 -Based Intermetallic Compounds (R = Rare Earth)," *Inorganic Chemistry*, 58(9), 5401-5405 (2019). DOI: 10.1021/acs.inorgchem.9b00480

Y. Yu, R. Liu, L. Zhang, G. Yao, Q. Wang, J. Zhu, S. Yang, and W. Cui, "Enhanced Magnetocaloric Effects in $\text{Gd}_2\text{In}_{1-x}\text{Al}_x$ ($0.4 \leq x \leq 1$) System by the Hysteresis-Free Metamagnetism," *Journal of Magnetism and Magnetic Materials*, 524, 167648 (2021). DOI: 10.1016/j.jmmm.2020.167648

R. Liu, S. Sun, G. Yao, Q. Wang, P. Tong, J. Zhu, S. Yang, and W. Cui, "Nonhysteretic Metamagnetic Phase Transition in $\text{Ho}_2\text{In}_{1-x}\text{Al}_x$ ($0 \leq x \leq 0.4$) by Hetero-Structural Alloying," *Journal of Magnetism and Magnetic Materials*, 538, 168305 (2021). DOI: 10.1016/j.jmmm.2021.168305

S. Sun, R. Liu, G. Yao, Z. Chen, Q. Wang, J. Zhu, S. Yang, and W. Cui, "Magnetic Phase Transition and Magnetic Properties in Rare-Earth-Based RAl_3C_3 Layered Carbides," *Journal of Magnetism and Magnetic Materials*, 540, 168445 (2021). DOI: 10.1016/j.jmmm.2021.168445