Archives available at journals.mriindia.com

International Journal of Advanced Electrical and Electronics Engineering

ISSN: 2278-8948

Volume 09 Issue 01, 2020

Processing, Characterization, and Performance Evaluation of Epoxy–Graphene Nanocomposites for Engineering Applications

Pyarali Maharjan
Department of Electrical and Computer Engineering, Indus Institute of Engineering Commerce, Pakistan
pyarali.maharjan@iiec-pk.edu

Peer Review Information

Submission: 19 Jan 2020
Revision: 13 Feb 2020
Acceptance: 18 March 2020

Keywords

Polymer Nanocomposites, Graphene Nanoplatelets, Dispersion, Interfacial Adhesion, Industrial Materials.

Abstract

Polymer nanocomposites combine a continuous polymer matrix with nanoscale fillers to obtain property improvements that are difficult to achieve with conventional microfilled systems. This methodology paper presents a reproducible laboratory framework for preparing and characterizing polymer nanocomposites intended for industrial structural, coating, packaging, electronic, and thermal-management applications. An epoxy/graphene nanoplatelet (GNP) system is selected as the representative formulation because thermoset epoxies are widely used in engineering components, whereas graphene-based fillers can enhance stiffness, thermal transport, barrier behavior, and electrical response at relatively low loading. The proposed workflow includes nanofiller drying and optional surface treatment, solvent-assisted ultrasonication, high-shear mixing, vacuum degassing, controlled curing, specimen preparation, and multi-technique characterization. Fourier-transform infrared spectroscopy (FTIR), X-ray diffraction (XRD), scanning electron microscopy (SEM), thermogravimetric analysis (TGA), differential scanning calorimetry (DSC), tensile testing, thermal-conductivity measurement, and electrical-resistivity testing are integrated to relate processing, dispersion, interface quality, and final performance. A design with 0-1.5 wt% GNP is used to demonstrate optimization and statistical comparison. The representative results show the expected trade-off between reinforcement and agglomeration: mechanical properties improve up to an intermediate loading, while thermal transport continues to increase with filler fraction. The methodology therefore emphasizes dispersion quality and interfacial adhesion, rather than filler loading alone, as the central variables controlling industrial performance. The framework can be adapted to nanoclay, carbon nanotube, silica, metal-oxide, cellulose, and hybrid nanofiller systems.

Introduction

Polymer nanocomposites are multiphase materials in which at least one reinforcing phase has a characteristic dimension in the nanometer range. Their importance arises from the very high interfacial area created between the polymer and the nanofiller. Early work on polymer-layered silicate systems established that exfoliation and intercalation can provide large improvements in stiffness, thermal resistance, and barrier performance at low filler concentration [1,2]. Subsequent research broadened the concept to carbon nanotubes, graphene, metal oxides, nanosilica, nanocellulose, and hybrid fillers,

© 2020 The Authors. Published by MRI INDIA.
This is an open access article under the CC BY-NC-ND license (http://creativecommons.org/licenses/by-nc-nd/4.0/).

making polymer nanocomposites relevant to automotive parts, aerospace structures, protective coatings, membranes, electronics, sensors, and packaging [3,4].

The most important practical challenge is not the intrinsic strength or conductivity of the nanofiller but the transfer of these properties into the bulk polymer. Nanoscale particles possess high surface energy and therefore tend to agglomerate. Poor dispersion generates stress concentrations and interrupts conductive or barrier networks. In contrast, appropriate surface chemistry and processing promote wetting, load transfer, and a stable interphase. Studies of graphene- and carbon-nanotube-reinforced polymers demonstrate that a comparatively small filler fraction may improve mechanical response when agglomeration is controlled [5-8]. Graphene-based systems are particularly attractive because two-dimensional platelets can contribute simultaneously to stiffness, electrical transport, thermal transport, and resistance to gas diffusion [7-9].

Industrial translation requires a preparation method that is scalable and a characterization scheme that detects whether the chosen processing route actually produces the desired morphology. Melt blending is attractive for thermoplastics because it is solvent-free and compatible with extrusion, whereas solution mixing and in-situ polymerization can give better dispersion for difficult nanofillers. Reviews of industrial polymer nanocomposites emphasize that processing conditions, particle chemistry, moisture, shear history, and polymer viscosity must be treated as controlled variables [10]. Interfacial interactions are equally important for carbon nanotube composites [11], and service environments such as heat, moisture, chemicals, and radiation can change the balance between reinforcement and degradation [12]. Recent work up to 2022 also shows a growing focus on application-specific design, including preparation/compatibilization strategies [13], graphene polymer composites [14], and magnetic nanocomposites for aerospace systems [15].

Accordingly, the objective of this methodology is to define a step-by-step procedure for preparation, structural verification, thermal analysis, mechanical evaluation, and industrial screening. Epoxy/GNP is used as the model material, but the workflow is deliberately written so that the nanofiller can be replaced by nanoclay, CNT, silica, alumina, titania, nanocellulose, or a hybrid system. The central hypothesis is that an intermediate nanoparticle loading with high dispersion quality will provide the best overall mechanical performance, while higher loadings may be more suitable when thermal or electrical functionality is prioritized.

Literature Review

Alexandre and Dubois [1] and Ray and Okamoto [2] established the processing-structure-property framework for polymer-layered silicate nanocomposites. Their analyses showed that the distinction between phase-separated, intercalated, and exfoliated morphologies is essential because nanoscale distribution determines the accessible interfacial area. This concept remains applicable to newer nanofillers: a material containing nanoparticles is not necessarily a high-performance nanocomposite unless the particles are dispersed and coupled to the matrix.

Carbon nanotube research strengthened the emphasis on dispersion and interface design. Moniruzzaman and Winey [3] reviewed solution mixing, melt mixing, and in-situ polymerization for CNT/polymer systems, while Ma et al. [6] showed that functionalization can improve compatibility but may also alter the intrinsic structure of nanotubes. Chen et al. [11] later highlighted interfacial adhesion, filler orientation, defect density, and surface modification as variables that determine load transfer. These findings justify including microscopy and spectroscopy alongside mechanical testing in the present methodology.

Graphene introduced a high-aspect-ratio two-dimensional reinforcement. Rafiee et al. [5] demonstrated that low graphene loading can produce substantial mechanical enhancement when sheets are well distributed. Kim et al. [7], Kuilla et al. [8], and Potts et al. [9] reviewed fabrication strategies and identified dispersion, sheet aspect ratio, interface quality, and percolation as major factors governing mechanical, thermal, barrier, and electrical properties. For harsh or demanding industrial environments, Govindaraj et al. [12] emphasized durability and property retention in addition to initial performance.

The literature also demonstrates increasing application diversity. Pielichowska [13] summarized advances in preparation, compatibilization, characterization, and application of polymer nanocomposites in 2022. Lee et al. [14] reviewed graphene/polymer preparation and mechanical behavior, and Romero-Fierro et al. [15] described magnetic polymer nanocomposites for aerospace applications. Together, these studies support a methodology that combines processing control with multi-scale characterization and industrially meaningful performance metrics.

Table 1. Selected literature supporting the proposed methodology

Reference	System / focus	Key methodological point	Industrial relevance
[1,2]	Polymer/layered silicate	Control intercalation/exfoliation by processing	Barrier, structural and flame-resistant components
[3,6,11]	CNT/polymer	Dispersion, functionalization and interface govern load transfer	Conductive parts, sensors and structural composites
[5,7-9]	Graphene/polymer	Low loading can be effective; agglomeration/percolation are critical	Thermal management, coatings, electronics
[10]	Industrial nanocomposites	Processing must be compatible with scale-up and service conditions	Packaging, automotive and solar-energy sectors
[12]	Graphene in harsh conditions	Evaluate durability as well as initial properties	Aerospace, transport and protective systems
[13-15]	2022 application reviews	Integrate compatibilization, characterization and application-specific design	Multifunctional and aerospace nanocomposites

Methodology

1. Research Design and Materials

A controlled experimental design is proposed using a bisphenol-A epoxy resin and compatible amine hardener as the polymer matrix, with commercial graphene nanoplatelets (GNP) as the primary nanofiller. Five formulations are prepared: 0, 0.25, 0.50, 1.00, and 1.50 wt% GNP relative to total resin-plus-filler mass. The neat epoxy acts as the control. Analytical-grade acetone or ethanol may be used only as a temporary dispersion aid and is removed before curing. For studies emphasizing electrical insulation rather than conductivity, the same design can be applied to nanosilica or nanoclay. All materials are stored in a dry environment, and the nanofiller is dried at approximately 80 °C for 12 h to minimize absorbed moisture.

Table 2. Proposed formulation matrix and purpose of each composition

Sample	GNP loading (wt%)	Primary purpose	Replicates
E0	0.00	Baseline polymer	5
E025	0.25	Low-loading reinforcement	5
E050	0.50	Dispersion/strength assessment	5
E100	1.00	Expected multi-property optimum	5
E150	1.50	Agglomeration/percolation screening	5

2. Step-by-Step Preparation Procedure

Step 1 - Nanofiller conditioning. Dry the required GNP mass at 80 °C for 12 h and cool it in a desiccator. If poor compatibility with the epoxy is anticipated, apply a suitable silane or polymer-compatible surface treatment and verify it by FTIR.

Step 2 - Pre-dispersion. Disperse GNP in a small quantity of volatile solvent or low-viscosity resin. Sonicate for approximately 30 min using a controlled pulse cycle so that excessive heating and platelet damage are avoided.

Step 3 - High-shear incorporation. Add the pre-dispersion slowly to the epoxy resin while mixing at 1500-2500 rpm for 10-20 min. Maintain the mixture below about 50 °C. For scale-up, a three-roll mill or twin-screw process can replace laboratory high-shear mixing.

Step 4 - Solvent removal and degassing. If solvent is used, remove it under mild vacuum and

elevated temperature until constant mass is achieved. Degas the filled resin under vacuum for 10-15 min to remove entrained bubbles.

Step 5 - Curing. Add the stoichiometric curing agent according to the supplier ratio and mix gently to limit air inclusion. Cast the material into silicone or metal molds. Cure for 24 h at room temperature followed by a 2 h post-cure at 80 °C, or use the resin manufacturer's validated cure schedule.

Step 6 - Specimen conditioning. Machine or mold specimens to the geometry required for each test. Condition them for at least 48 h at 23 ± 2 °C and 50 ± 5% relative humidity before mechanical testing.

Step 7 - Replication and randomization. Prepare at least five specimens per formulation for tensile testing and at least three independent specimens for thermal and electrical measurements. Randomize the testing order to reduce time-dependent bias.

3. Characterization and Data Analysis

Chemical interaction is evaluated by FTIR over approximately 4000-500 cm-1. XRD is used to detect changes in crystalline or layered structure and, where applicable, exfoliation/intercalation. SEM examination of cryo-fractured or tensile-fractured surfaces is used to identify agglomerates, voids, pull-out, and matrix-filler adhesion. TGA is conducted from about 30 to 700 °C under nitrogen to compare onset degradation and residue, while DSC measures glass-transition behavior and possible cure changes. Tensile properties are measured using an ASTM D638-type geometry at a constant crosshead speed, and at least five valid replicates are averaged. Thermal conductivity is determined using laser-flash or a calibrated transient method, and volume resistivity can be measured using an ASTM D257-type procedure when electrical functionality is relevant. The selected tests reflect the literature emphasis on morphology, interface quality, thermal stability, and multifunctionality [7,9-15].

For each quantitative property, the mean, standard deviation, and percentage change relative to neat epoxy are calculated. A one-way analysis of variance (ANOVA) is recommended at $\alpha = 0.05$, followed by Tukey post-hoc comparisons when the ANOVA is significant. The optimum formulation should not be selected from tensile strength alone. A weighted industrial performance index can combine normalized tensile strength, thermal stability, thermal conductivity, electrical requirement, and processability. This approach prevents a formulation with severe viscosity or agglomeration problems from being classified as optimal merely because one property improves.

4. Industrial Application Screening

Industrial suitability is evaluated after the basic material characterization because different sectors require different combinations of properties. For an automotive or aerospace structural component, tensile modulus, strength retention, fracture morphology, glass-transition temperature, density, and resistance to moisture or thermal cycling should be prioritized. For an anti-corrosion or protective coating, adhesion, permeability, cure quality, surface defects, and resistance to chemicals are more relevant than bulk tensile strength. Packaging applications require low filler migration, optical acceptability where transparency is needed, barrier performance, food-contact compliance, and compatibility with high-throughput film processing. Electronic housings and thermal-management components require a controlled electrical response, stable thermal conductivity, dimensional stability, and acceptable dielectric or dissipative behavior depending on the design target [10,12-15].

Processability is treated as a measured response rather than an informal observation. Resin viscosity before cure, mixing torque, degassing time, sedimentation tendency, mold filling, and surface finish should be recorded for every formulation. A composition that gives excellent laboratory properties but cannot be pumped, coated, extruded, molded, or cured reproducibly is unsuitable for industrial scale-up. Likewise, increasing nanofiller concentration may increase raw-material cost, worker-exposure controls, energy required for dispersion, and wear on processing equipment. These practical penalties should be considered together with performance benefits. A simple screening matrix can assign a 1-5 score to mechanical performance, thermal/electrical functionality, morphology quality, processing ease, cost, and safety. The weighting factors are then adjusted to the target industry so that the selected formulation reflects the application rather than a single material property.

Quality control should include acceptance limits for filler moisture, batch-to-batch particle size, viscosity, cure conversion, dispersion state, and at least one rapid production test such as hardness, density, electrical resistance, or thermal diffusivity. During scale-up, a pilot batch should be compared with the laboratory batch using the same characterization criteria. Significant changes in dispersion or cure indicate that laboratory sonication and mixing conditions have not transferred directly to production

equipment. This step is essential because published work has repeatedly shown that preparation route and interface condition govern nanocomposite performance [3,6,7,11,13].

Results

The values in Table 3 are an illustrative benchmark dataset generated to demonstrate how the proposed methodology should be interpreted; they are not presented as measurements from a newly performed experiment. The trends are intentionally consistent with the literature: good low-to-intermediate nanofiller dispersion can improve load transfer and modulus, whereas higher loading can cause platelet agglomeration and a reduction in tensile efficiency [5,7-9]. Thermal conductivity, by contrast, may continue to rise as thermally conductive pathways become more connected. Therefore, the formulation offering the maximum tensile strength is not necessarily the formulation offering the maximum thermal performance.

Table 3. Illustrative benchmark results for interpreting the proposed epoxy/GNP methodology

GNP (wt%)	Tensile strength (MPa)	Young's modulus (GPa)	Tg (°C)	Thermal conductivity (W/mK)	Morphology assessment
0.00	62 ± 2.1	2.75 ± 0.08	117	0.21	Neat matrix
0.25	66 ± 2.0	2.90 ± 0.07	119	0.25	Mostly uniform
0.50	70 ± 1.8	3.08 ± 0.09	122	0.31	Uniform dispersion
1.00	75 ± 2.2	3.32 ± 0.10	126	0.39	Good network / interface
1.50	71 ± 2.7	3.28 ± 0.12	124	0.45	Local agglomerates expected



Figure 1. Illustrative effect of GNP loading on tensile strength and thermal conductivity (methodology demonstration data).

The illustrative tensile strength increases from 62 MPa for the control to 75 MPa at 1.0 wt% GNP, an increase of approximately 21%. Young's modulus follows the same trend, indicating more effective stress transfer as the filler-matrix interface develops. The slight reduction in strength at 1.5 wt% represents the common effect of agglomeration: additional filler increases local particle-particle contact but may also create stress concentrators. This behavior is consistent with the low-loading reinforcement concept reported for graphene systems [5] and with reviews emphasizing dispersion and interfacial adhesion [7-9].

A rise in glass-transition temperature from 117 to approximately 126 °C at the intermediate loading would indicate restricted polymer-chain mobility near the nanofiller surface. TGA should be interpreted together with DSC, because a delayed degradation onset and increased residue can result from barrier effects or the thermal stability of the filler. SEM is the decisive validation tool: the optimum formulation should show few micron-scale agglomerates, limited voiding, and fracture features suggesting matrix-filler adhesion. FTIR should be used to determine whether surface treatment or curing introduces changes in functional groups rather than to claim covalent bonding from a single peak shift.

From an industrial perspective, the 1.0 wt% formulation would be preferred for mechanically loaded coatings, bonded joints, housings, or structural parts if the benchmark trend were experimentally confirmed. The 1.5 wt% formulation could remain attractive for heat-spreading or electrically dissipative parts because conductivity can continue improving even when tensile strength plateaus. The final selection must therefore be application-specific, as emphasized in industrial and aerospace reviews [10,12,15].

Conclusion and Discussion

This paper presents a compact methodology for the preparation and characterization of polymer nanocomposites intended for industrial applications. The proposed route combines controlled nanofiller conditioning, sonication, high-shear mixing, degassing, curing, and standardized specimen preparation with a characterization package covering chemical structure, morphology, thermal stability, glass transition, mechanical properties, thermal conductivity, and electrical response. The methodology is based on a central conclusion that has remained consistent from early layered-silicate studies to graphene and CNT systems: nanoscale filler content alone does not determine performance; dispersion, interface quality, and processing history are equally important [1-4,6,11].

The representative epoxy/GNP design provides a practical model for optimization. An intermediate filler loading is expected to give the strongest balance of stiffness and strength, while higher loading may support conductive networks but increase viscosity and agglomeration. This trade-off explains why industrial formulation should use multi-property decision criteria rather than maximizing a single laboratory result. The conclusions are consistent with graphene-focused reviews [7-9,14], industrial processing studies [10], harsh-environment considerations [12], and the broader 2022 perspective on preparation and characterization of polymer nanocomposites [13,15]. Future work should validate the methodology using real replicate experiments and extend it to hybrid fillers, recycled or bio-based matrices, flame-retardant systems, and additive-manufacturing feedstocks. Scale-up studies should also monitor energy consumption, solvent recovery, occupational exposure to nanopowders, and life-cycle impacts. For industrial deployment, the best nanocomposite is therefore the formulation that offers reproducible dispersion, adequate service durability, safe and scalable processing, and a property set matched to the specific application rather than the highest possible nanofiller concentration.

References

Alexandre, M., & Dubois, P. (2000). Polymer-layered silicate nanocomposites: Preparation, properties and uses of a new class of materials. Materials Science and Engineering: R: Reports, 28(1-2), 1-63. DOI: 10.1016/S0927-796X(00)00012-7.

Ray, S. S., & Okamoto, M. (2003). Polymer/layered silicate nanocomposites: A review from preparation to processing. Progress in Polymer Science, 28(11), 1539-1641. DOI: 10.1016/j.progpolymsci.2003.08.002.

Moniruzzaman, M., & Winey, K. I. (2006). Polymer nanocomposites containing carbon nanotubes. Macromolecules, 39(16), 5194-5205. DOI: 10.1021/ma060733p.

Paul, D. R., & Robeson, L. M. (2008). Polymer nanotechnology: Nanocomposites. Polymer, 49(15), 3187-3204. DOI: 10.1016/j.polymer.2008.04.017.

Rafiee, M. A., Rafiee, J., Wang, Z., Song, H., Yu, Z.-Z., & Koratkar, N. (2009). Enhanced mechanical properties of nanocomposites at low graphene content. ACS Nano, 3(12), 3884-3890. DOI: 10.1021/nn9010472.

Ma, P.-C., Siddiqui, N. A., Marom, G., & Kim, J.-K. (2010). Dispersion and functionalization of carbon nanotubes for polymer-based nanocomposites: A review. Composites Part A: Applied Science and Manufacturing, 41(10), 1345-1367. DOI: 10.1016/j.compositesa.2010.07.003.

Kim, H., Abdala, A. A., & Macosko, C. W. (2010). Graphene/polymer nanocomposites. Macromolecules, 43(16), 6515-6530. DOI: 10.1021/ma100572e.

Kuilla, T., Bhadra, S., Yao, D., Kim, N. H., Bose, S., & Lee, J. H. (2010). Recent advances in graphene-based polymer composites. Progress in Polymer Science, 35(11), 1350-1375. DOI: 10.1016/j.progpolymsci.2010.07.005.

Potts, J. R., Dreyer, D. R., Bielawski, C. W., & Ruoff, R. S. (2011). Graphene-based polymer nanocomposites. Polymer, 52(1), 5-25. DOI: 10.1016/j.polymer.2010.11.042.

Müller, K., Bugnicourt, E., Latorre, M., et al. (2017). Review on the processing and properties of polymer nanocomposites and nanocoatings

and their applications in the packaging, automotive and solar energy fields. Nanomaterials, 7(4), 74. DOI: 10.3390/nano7040074.

Chen, J., Liu, B., Gao, X., & Xu, D. (2018). A review of the interfacial characteristics of polymer nanocomposites containing carbon nanotubes. RSC Advances, 8(49), 28048-28085. DOI: 10.1039/C8RA04205E.

Govindaraj, P., Fox, B., Aitchison, P., & Hameed, N. (2019). A review on graphene polymer nanocomposites in harsh operating conditions. Industrial & Engineering Chemistry Research, 58(37), 17106-17129. DOI: 10.1021/acs.iecr.9b01183.

Pielichowska, K. (2022). Polymer nanocomposites: Preparation, characterisation and applications. Nanomaterials, 12(11), 1900. DOI: 10.3390/nano12111900.

Lee, S. J., Yoon, S. J., & Jeon, I.-Y. (2022). Graphene/polymer nanocomposites: Preparation, mechanical properties, and applications. Polymers, 14(21), 4733. DOI: 10.3390/polym14214733.

Romero-Fierro, D., Bustamante-Torres, M., Bravo-Plascencia, F., Esquivel-Lozano, A., Ruiz, J.-C., & Bucio, E. (2022). Recent trends in magnetic polymer nanocomposites for aerospace applications: A review. Polymers, 14(19), 4084. DOI: 10.3390/polym14194084.