



Additive Manufacturing Techniques for Rapid Prototyping in Mechanical Engineering Applications

Branislav Fazlioglu

Department of Electrical and Computer Engineering, Andaman Polytechnic for Technology and Trade, Thailand

branislav.fazlioglu@aptt-th.net

Peer Review Information

Submission: 01 Jan 2019

Revision: 16 Feb 2019

Acceptance: 03 March 2019

Keywords

*Additive manufacturing,
Rapid prototyping, Fused
deposition modeling,
Stereolithography,
Mechanical engineering*

Abstract

Additive manufacturing (AM) has transformed rapid prototyping by enabling mechanical engineers to convert digital models into physical components without dedicated tooling. This methodology paper develops a literature-grounded framework for selecting and evaluating AM techniques for rapid prototyping in mechanical engineering applications, with emphasis on fused deposition modeling/fused filament fabrication (FDM/FFF), stereolithography (SLA), and selective laser sintering (SLS). The proposed procedure integrates design requirements, CAD model preparation, tessellation and slicing, process and material selection, fabrication, post-processing, dimensional inspection, functional assessment, and multi-criteria comparison of quality, time, and cost. The framework is intended for concept models, fit-and-assembly prototypes, and functional engineering prototypes. Published work demonstrates that AM can shorten iteration cycles and enable geometries that are difficult to manufacture conventionally, although process-dependent anisotropy, surface finish, dimensional deviation, and material limitations remain important design constraints [1], [6], [9]. A qualitative synthesis shows that FDM is particularly attractive for economical concept and fit testing, SLA is preferred where surface finish and geometric detail dominate, and SLS is advantageous for complex functional polymer prototypes because surrounding powder reduces support-structure constraints. The study provides a reproducible decision pathway that can be adapted to laboratory testing or industrial prototype development while restricting the supporting literature to publications available through 2019.

Introduction

Rapid prototyping is a central activity in mechanical product development because early physical models expose geometric conflicts, assembly errors, ergonomic problems, and functional weaknesses before expensive tooling or production decisions are made. Traditional prototype routes such as CNC machining, casting, or fabricated mock-ups remain valuable, but they can require multiple setups, fixtures, specialist labor, or geometry-specific tooling. AM changes this workflow by creating a part directly from

digital geometry through sequential material addition. Wong and Hernandez [1] describe the basic digital chain from computer-aided design (CAD) through tessellation and layer generation, while Huang et al. [2] emphasize the broader effect of AM on customization, distributed production, and reduced dependence on conventional tooling.

For mechanical engineering, the value of AM is not limited to visual models. Prototypes may be required to verify interfaces, evaluate motion,

test load paths, check manufacturability, demonstrate mechanisms, or support design reviews. The appropriate AM technique therefore depends on the purpose of the prototype. A low-cost FDM part may be adequate for envelope and fit verification, whereas a high-detail SLA part can be preferable for fluidic channels, housings, or form studies. Powder-bed methods such as SLS can produce complex polymer parts with fewer support-related restrictions and may be more suitable for functional assemblies. These advantages must be balanced against process-specific limits in accuracy, anisotropy, surface texture, post-processing, and material performance [3], [4], [9].

The objective of this paper is to present a step-by-step methodology for applying AM to rapid prototyping in mechanical engineering. The approach is organized around three questions: what the prototype must prove, which AM process best addresses that requirement, and how the resulting prototype should be evaluated. The paper focuses on a practical comparative framework rather than claiming new laboratory measurements. The results section therefore reports a literature-grounded technique-selection synthesis that can be used as a baseline for future experimental work. All references used were published in 2019 or earlier, in accordance with the defined literature boundary.

Literature Review

Early AM research established the importance of build orientation and layer-wise bonding in determining prototype performance. Ahn et al. [3] showed that FDM ABS exhibits anisotropic behavior, demonstrating that mechanical response cannot be treated as identical in all directions. This finding is directly relevant to rapid prototyping because a part that accurately reproduces geometry may still misrepresent functional behavior if load direction and raster organization are ignored. Sood et al. [4] further demonstrated that FDM process variables interact to influence tensile, flexural, and impact behavior, reinforcing the need to treat slicing parameters as engineering variables rather than merely machine settings.

The emergence of lower-cost material-extrusion systems widened access to rapid prototyping, but also increased concern regarding repeatability. Tymrak et al. [5] investigated components fabricated on open-source 3-D printers under realistic conditions and showed that usable mechanical properties can be achieved, while also illustrating variability associated with machine configuration, material, and build

conditions. For a methodology intended for general mechanical engineering laboratories, this evidence supports the inclusion of repeat builds, standardized measurement locations, and explicit recording of machine and slicing parameters.

Design practice also changed as AM matured. Thompson et al. [6] reviewed design for additive manufacturing (DfAM) and argued that AM design decisions should account for both opportunities and constraints, including geometric freedom, support generation, process limitations, material behavior, and cost. This is especially important in rapid prototyping because a prototype may be designed either to mimic a conventionally manufactured production part or to exploit AM-specific geometry. The methodology proposed in this paper distinguishes these objectives: design-validation prototypes should preserve production intent, whereas exploratory prototypes may deliberately use topology changes, part consolidation, or internal complexity to examine alternative solutions.

Process-parameter studies also improved understanding of polymer AM. Chacón et al. [7] examined PLA structures produced by fused deposition modelling and reported strong dependencies between process parameters, build orientation, and mechanical performance. Their work supports the selection of layer thickness, orientation, raster strategy, and infill as controlled factors when functional prototypes are evaluated. In parallel, Attaran [8] summarized the advantages of 3-D printing relative to traditional manufacturing, including reduced tooling dependence, customization, design complexity, and shorter product-development cycles. These advantages explain why AM is particularly effective during iterative engineering development, where multiple design revisions may be required before the geometry is frozen.

Ngo et al. [9] provided a broad review of AM materials, processes, applications, and challenges. Their synthesis is useful for process selection because it shows that no single AM technique is universally superior; performance depends on the interaction among feedstock, energy or deposition mechanism, resolution, geometry, and end-use requirement. By 2019, comparative manufacturing studies were also directly examining when AM should be preferred. Pereira et al. [10] compared additive and traditional manufacturing and emphasized that the “best” method depends on part quantity, complexity, customization, and process

economics. For rapid prototyping, where quantity is low and iteration value is high, AM often has a strong advantage, but final selection should still consider dimensional, surface, functional, and cost criteria.

The literature therefore points to a clear methodological gap between having access to a 3-D printer and engineering an effective prototype-development process. A robust approach must connect prototype purpose to geometry preparation, process selection, build parameters, post-processing, inspection, and decision criteria. The framework below consolidates these elements into a reproducible sequence suitable

for teaching laboratories, design offices, and early-stage product development.

Methodology

The proposed methodology uses a comparative case-study structure. A common mechanical benchmark component is designed with features that are representative of rapid-prototyping tasks: planar walls, a cylindrical boss, two through-holes, a thin rib, a snap/clearance feature, an overhang, and a mating interface. The same nominal CAD model is then prepared for FDM, SLA, and SLS so that process differences can be evaluated against a common design intent. The workflow is shown in Figure 1.




Figure 1. Step-by-step methodology for AM-based rapid prototyping in mechanical engineering.

Step 1 - Define prototype purpose and engineering requirements. The study begins by stating what must be learned from the prototype. Requirements are grouped as visual/form verification, fit and assembly, motion or ergonomic assessment, and functional/mechanical testing. Critical dimensions, load directions, contact surfaces, temperature exposure, required surface condition, target lead time, and allowable prototype cost are recorded. This prevents the common error of selecting a printer before defining what the prototype must demonstrate. For a fit prototype, dimensional stability may dominate; for a functional bracket, orientation-sensitive strength becomes a primary constraint [3], [7].

Step 2 - Create and check the CAD benchmark model. A parametric solid model is generated in standard mechanical CAD software. Dimensions are assigned from the design specification rather than from printer capability. Features smaller than the selected process can reliably reproduce are flagged, but they are not automatically enlarged unless the prototype objective permits design adaptation. The CAD model is checked for closed volumes, interference, minimum wall thickness, and assembly clearances. A controlled revision code is used so that all printed specimens correspond to the same geometry.

Step 3 - Export, tessellate, orient, and slice the digital model. The model is exported to STL or an equivalent mesh format using a tolerance fine enough to avoid visible faceting on curved features. The mesh is inspected for holes, inverted normals, intersecting surfaces, and non-manifold edges. Orientation is then selected according to the prototype objective. For FDM, orientations that place major tensile loads across weak interlayer interfaces are avoided where functional behavior is important [3], [4]. For SLA, orientation is balanced against support scars and drainage. For SLS, orientation is selected to control packing, thermal behavior, and surface exposure while benefiting from powder support.

Step 4 - Select process, material, and controlled build parameters. Three process families are compared: FDM/FFF using a common engineering thermoplastic such as PLA or ABS; SLA using an engineering photopolymer; and SLS using a polymer powder such as nylon. The controlled parameter sheet records layer thickness, orientation, infill or shell strategy where applicable, support strategy, print speed or machine profile, build temperature/energy profile where accessible, and material batch. The literature shows that parameter settings can materially affect mechanical properties and dimensional response, particularly in extrusion-based AM [4], [7].

Step 5 - Fabricate and post-process prototypes. At least three repeat prototypes per process are recommended for a laboratory study so that measurement scatter can be observed. Machine warm-up, calibration, and material conditioning follow the manufacturer procedure. After fabrication, FDM supports are removed mechanically, SLA parts are washed and post-cured according to resin requirements, and SLS parts are depowdered. Post-processing time is recorded separately from machine build time because a rapid-prototyping method that prints quickly but requires substantial finishing may not minimize total iteration time.

Step 6 - Inspect geometry, fit, surface condition, and functional behavior. Dimensional verification is performed with calibrated calipers, micrometers, gauges, or coordinate measurement equipment depending on tolerance. At minimum, three linear dimensions, one-hole diameter, and one mating feature are measured at predefined locations. Surface condition is assessed on a designated face using profilometry when available or by a controlled visual/tactile scale for teaching laboratories. Assembly fit is classified as pass, conditional pass, or fail. If functional testing is required, loading follows the actual service direction and build orientation is documented because AM anisotropy can significantly influence interpretation [3], [5].

Step 7 - Evaluate lead time, cost, and technique suitability. Total prototype lead time is calculated as data preparation plus machine setup plus build time plus cooling/curing plus support removal and finishing. Direct prototype cost includes material consumed, support or waste material, machine time, and post-processing consumables; labor may be added where comparative costing is required. Technical suitability is then judged using the same criteria for all processes: dimensional fidelity, surface quality, functional suitability, geometric freedom, post-processing burden, lead time, and cost. A weighted decision matrix can be used when one criterion is more important than another. This final selection logic is consistent with DfAM and manufacturing-method comparisons reported in the literature [6], [10].

Results

Because this paper presents a methodology rather than a completed laboratory campaign, the results are reported as a literature-grounded comparative outcome of the proposed selection framework. Table 1 summarizes the expected relative behavior of the three process families for rapid prototyping. The entries are qualitative rankings synthesized from the cited literature and established process characteristics; they are not presented as new measured data. This distinction is important because actual dimensional error, roughness, build time, and cost depend on machine model, material, geometry, orientation, and parameter settings.

Table 1. Literature-grounded comparison of AM techniques for rapid prototyping [1], [6], [7], [9], [10].

Criterion	FDM/FFF	SLA	SLS	Rapid-prototyping implication
Prototype cost	Low	Moderate	Moderate to high	FDM is attractive for frequent low-cost design iterations.
Surface/detail quality	Moderate	High	Good	SLA is preferred for fine features, visual form, and smooth surfaces.
Functional polymer use	Good, but orientation-sensitive	Resin-dependent; can be brittle	High for complex polymer parts	SLS is strong for functional geometry; FDM requires orientation control.
Support burden	Supports often required	Supports generally required	Powder is self-supporting	SLS handles internal/complex geometry with fewer support restrictions.
Dimensional/fit studies	Good with calibration	Very good	Good	SLA is strong where small-feature fidelity is the dominant requirement.
Best mechanical-engineering role	Concept, fit, fixtures, low-cost functional models	High-detail housings, form studies, precise prototypes	Complex functional prototypes and assemblies	Selection should follow the prototype objective rather than printer availability.

The comparative outcome indicates that FDM/FFF provides the most practical starting

point when the main objective is inexpensive iteration. Its accessibility and low material cost

support repeated design changes, but mechanical interpretation must account for directional properties and the effects of process settings [3]-[5], [7]. This makes FDM particularly effective for layout models, brackets, jigs, fixtures, fit checks, and early functional trials when the designer controls orientation and does not assume bulk-material isotropy.

SLA becomes the preferred route when feature definition and surface condition are more important than the lowest cost. It is therefore well suited to compact housings, interface models, flow-path demonstrations, aesthetic/ergonomic surfaces, and prototypes requiring small details. However, prototype function must be interpreted in relation to the selected resin and post-cure condition. SLS provides a different advantage: powder surrounding the part reduces the need for discrete support structures, which makes the method attractive for complex geometries, nested features, and functional polymer prototypes where support removal could damage or obstruct the geometry. These process differences illustrate the central result of the methodology: rapid prototyping should be treated as a requirement-driven process-selection problem, not as a single-technology activity [6], [9].

The framework also clarifies the relationship between AM and conventional methods. For low-volume prototypes with frequent design revisions, AM avoids dedicated tooling and can compress the design-build-evaluate loop. As volume increases or when material properties and tolerances exceed the capability of the selected AM route, machining, molding, or hybrid processing may become more appropriate. Pereira et al. [10] similarly show that manufacturing choice must be contextual rather than absolute, while Attaran [8] emphasizes the strategic value of rapid iteration and customization. Thus, the principal performance gain of AM in prototyping is not merely “faster printing”; it is faster learning per design iteration.

An important outcome of the proposed framework is that the preferred process changes when the prototype objective is re-weighted. If the primary requirement is frequent geometric iteration at minimum expense, cost and turnaround receive the largest weights and FDM generally becomes the preferred route. If the objective is to verify fine interfaces, small holes, sealing surfaces, or visual detail, dimensional and surface criteria receive greater weight and SLA becomes more attractive. Where the prototype contains enclosed passages, interlocking

features, or complex free-form geometry that would be difficult to support and clean, SLS can gain priority because the powder bed supports the build during fabrication. The decision process therefore makes trade-offs explicit and traceable rather than relying on informal printer preference.

The framework also separates machine build time from total iteration time. In practice, engineering teams often compare AM systems only by nominal print duration; however, data preparation, support generation, queue time, cooling, washing, curing, depowdering, support removal, and dimensional inspection can substantially affect when a prototype becomes usable. For rapid product development, the more meaningful metric is elapsed time from approved CAD revision to a prototype that can be evaluated. The same reasoning applies to cost: material price alone does not capture machine occupancy, failed builds, support waste, finishing labor, or the cost of repeating a prototype after a design change. Recording these elements improves the value of the method for industrial decision making [8], [10].

A further result concerns interpretation of prototype function. A rapid prototype should not automatically be treated as a production-equivalent component. In FDM, interlayer bonding and raster orientation can alter stiffness and strength [3], [4], [7]; in photopolymer systems, resin formulation and post-cure condition influence behavior; and in powder-bed processing, thermal history and surface condition may differ from those of conventionally processed polymers. Consequently, the prototype acceptance criterion must match the decision being made. A geometry-validation model can be accepted primarily on dimensional and assembly evidence, whereas a load-bearing prototype requires a material and build strategy that provides a defensible representation of service behavior.

Conclusion and Discussion

This paper presented a step-by-step methodology for using additive manufacturing in rapid prototyping for mechanical engineering applications. The proposed sequence starts with the engineering question that the prototype must answer and then links CAD preparation, model checking, process selection, build-parameter control, fabrication, post-processing, inspection, functional evaluation, and time-cost assessment. This structure is intentionally process-neutral: FDM, SLA, and SLS are treated as alternative tools that solve different prototyping problems rather

than as competing technologies with a universal winner. The literature through 2019 supports three central conclusions. First, extrusion-based AM is highly useful for economical iteration but is sensitive to build direction and process settings, so anisotropy must be considered when a prototype is used for functional decisions [3], [4], [7]. Second, DfAM principles are necessary even in prototyping because orientation, support strategy, geometry, and material behavior influence whether the printed artifact actually represents the intended design question [6]. Third, the economic advantage of AM is strongest when complexity, customization, low quantity, and rapid design change are valued, while conventional methods can remain preferable for higher production volumes or when demanding production-grade properties dominate [8], [10]. For practical implementation, engineers should therefore define acceptance criteria before printing and should record the fully digital-to-physical process. Future experimental studies can extend this methodology by collecting replicated dimensional-error data, profilometer measurements, tensile or flexural test results, actual energy consumption, and total prototype cost for specific machines and materials. Those measurements can then replace the qualitative comparison in Table 1 and permit statistical analysis. The methodology remains useful as the control structure for such work because it makes the prototype objective, process variables, inspection method, and decision criteria explicit.

References

- K. V. Wong and A. Hernandez, "A Review of Additive Manufacturing," *ISRN Mechanical Engineering*, vol. 2012, Article ID 208760, 2012. DOI: 10.5402/2012/208760
- S. H. Huang, P. Liu, A. Mokasdar, and L. Hou, "Additive manufacturing and its societal impact: a literature review," *The International Journal of Advanced Manufacturing Technology*, vol. 67, pp. 1191–1203, 2013. DOI: 10.1007/s00170-012-4558-5
- S.-H. Ahn, M. Montero, D. Odell, S. Roundy, and P. K. Wright, "Anisotropic material properties of fused deposition modeling ABS," *Rapid Prototyping Journal*, vol. 8, no. 4, pp. 248–257, 2002. DOI: 10.1108/13552540210441166
- K. Sood, R. K. Ohdar, and S. S. Mahapatra, "Parametric appraisal of mechanical property of fused deposition modelling processed parts," *Materials & Design*, vol. 31, no. 1, pp. 287–295, 2010. DOI: 10.1016/j.matdes.2009.06.016
- M. Tymrak, M. Kreiger, and J. M. Pearce, "Mechanical properties of components fabricated with open-source 3-D printers under realistic environmental conditions," *Materials & Design*, vol. 58, pp. 242–246, 2014. DOI: 10.1016/j.matdes.2014.02.038
- M. K. Thompson et al., "Design for Additive Manufacturing: Trends, opportunities, considerations, and constraints," *CIRP Annals*, vol. 65, no. 2, pp. 737–760, 2016. DOI: 10.1016/j.cirp.2016.05.004
- J. M. Chacón, M. A. Caminero, E. García-Plaza, and P. J. Núñez, "Additive manufacturing of PLA structures using fused deposition modelling: Effect of process parameters on mechanical properties and their optimal selection," *Materials & Design*, vol. 124, pp. 143–157, 2017. DOI: 10.1016/j.matdes.2017.03.065
- M. Attaran, "The rise of 3-D printing: The advantages of additive manufacturing over traditional manufacturing," *Business Horizons*, vol. 60, no. 5, pp. 677–688, 2017. DOI: 10.1016/j.bushor.2017.05.011
- T. D. Ngo, A. Kashani, G. Imbalzano, K. T. Q. Nguyen, and D. Hui, "Additive manufacturing (3D printing): A review of materials, methods, applications and challenges," *Composites Part B: Engineering*, vol. 143, pp. 172–196, 2018. DOI: 10.1016/j.compositesb.2018.02.012
- T. Pereira, J. V. Kennedy, and J. Potgieter, "A comparison of traditional manufacturing vs additive manufacturing, the best method for the job," *Procedia Manufacturing*, vol. 30, pp. 11–18, 2019. DOI: 10.1016/j.promfg.2019.02.003